

Technical Data Sheet

Accucomp ABS801L

Acrylonitrile Butadiene Styrene
LyondellBasell Industries
Engineering Plastics

General			
Features	• Medium Impact Resistance		
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.04	1.04 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 Kg)	2.0 g/10 min	2.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	276000 psi	1900 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	5370 psi	37.0 MPa	
Break	5080 psi	35.0 MPa	
Tensile Elongation			ASTM D638
Yield	3.0 %	3.0 %	
Break	14 %	14 %	
Flexural Modulus	377000 psi	2600 MPa	ASTM D790
Flexural Strength	9140 psi	63.0 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	4.8 ft·lb/in	260 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	102	102	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	183 °F	84.0 °C	
264 Psi (1.8 Mpa), Unannealed	163 °F	73.0 °C	

Notes

These are typical property values not to be construed as specification limits.