

Technical Data Sheet

Ronfalin ABS RT51 GRY73790



Acrylonitrile Butadiene Styrene

Product Description

Ronfalin RT51 GREY 73790 is a Acrylonitrile Butadiene Styrene material. Features include: Good Toughness, and Medium Rigidity.

Attribute Good Toughness; Medium Rigidity

Application Electrical Parts; Housings

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (220 °C/10.0 kg)	17	g/10 min	ISO 1133
Density	1.05	g/cm ³	ISO 1183
Mechanical			
Tensile Stress at Yield, (50 mm/min)	48.0	MPa	ISO 527-2
Flexural Modulus	2500	MPa	ISO 178
Impact			
Notched Izod Impact Strength, (Type 1, Notch A)	22	kJ/m ²	ISO 180
Hardness			
Ball Indentation Hardness	102	MPa	ISO 2039-1
Thermal			
Vicat Softening Temperature, (B (50N), 50 °C/h)	100	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa)	99	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa)	97	°C	ISO 75-2/A
Electrical			
Dielectric Strength	>25	kV/mm	IEC 60243-1
Comparative Tracking Index (CTI), (Solution A)	>600	V	IEC 60112
Surface Resistivity	1E+16	ohm	IEC 60093
UL Information			
Flame Rating, (1.6 mm)	HB		UL 94