

Technical Data Sheet

Schulamid 6 GB 15 U

Polyamide 6
LyondellBasell Industries
Engineering Plastics

Product Description

15% glass bead reinforced Polyamide 6 compound, UV-stabilized

General


Filler / Reinforcement	• Glass Bead, 15% Filler by Weight
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA6-GB

Physical	Dry	Conditioned	Unit	Test Method
Density	1.23	--	g/cm ³	ISO 1183/A
Viscosity Number	145	--	cm ³ /g	ISO 307
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	493000 (3400)	138000 (950)	psi (MPa)	ISO 527-1/1A/1
Tensile Stress (Break)	10400 (72.0)	6090 (42.0)	psi (MPa)	ISO 527-2/1A/5
Tensile Strain (Break)	9.0	> 50	%	ISO 527-2/1A/5
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F (-30°C)	1.7 (3.5)	--	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	2.4 (5.0)	7.6 (16)	ft·lb/in ² (kJ/m ²)	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F (-30°C)	12 (26)	--	ft·lb/in ² (kJ/m ²)	
73°F (23°C)	21 ft·lb/in ² (45 kJ/m ²)	No Break	(kJ/m ²)	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
66 Psi (0.45 Mpa), Unannealed	329 (165)	--	°F (°C)	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	140 (60.0)	--	°F (°C)	ISO 75-2/Af
Vicat Softening Temperature				
--	378 (192)	--	°F (°C)	ISO 306/B50
--	410 (210)	--	°F (°C)	ISO 306/A50
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate				
0.0787 In (2.00 Mm)	2.4 (60)	--	in/min (mm/min)	ISO 3795
0.0787 In (2.00 Mm)	2.4 (60)	--	in/min (mm/min)	FMVSS 302

Technical Data Sheet

Schulamid 6 GB 15 U

Polyamide 6
LyondellBasell Industries
Engineering Plastics



Injection	Dry (English)	Dry (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Processing (Melt) Temp	482 to 536 °F	250 to 280 °C
Mold Temperature	140 to 212 °F	60 to 100 °C

Notes

These are typical property values not to be construed as specification limits.