

Technical Data Sheet

SCHULAREC PA 66 GF 30 H

Polyamide 66

Product Description

30% glass fiber reinforced and heat stabilized, recycled grade

General

Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.34 to 1.38 g/cm ³	1.34 to 1.38 g/cm ³	ISO 1183/A
Molding Shrinkage			ISO 294-4
Across Flow	0.80 to 1.2 %	0.80 to 1.2 %	
Flow	0.30 to 0.50 %	0.30 to 0.50 %	
Water Absorption - (23°C, water)	5.0 to 7.0 %	5.0 to 7.0 %	GE
Viscosity Number			ISO 307
96% H2SO4 (Sulphuric Acid)	125 to 145 cm ³ /g	125 to 145 cm ³ /g	
Humidity Absorption - (23°C, 50% R. H.)	1.4 to 2.2 %	1.4 to 2.2 %	ISO 62
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	1.26E+6 psi	8700 MPa	ISO 527-2/1A/1
Tensile Stress (Break)	21800 psi	150 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	2.9 %	2.9 %	ISO 527-2/1A/5
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	2.9 ft·lb/in ²	6.0 kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
73°F (23°C)	24 ft·lb/in ²	50 kJ/m ²	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Melting Temperature ¹	500 °F	260 °C	ISO 11357-3
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flame Rating			ISO 1210
0.031 in (0.8 mm)	HB	HB	
0.06 in (1.6 mm)	HB	HB	
Additional Information	Nominal Value (English)	Nominal Value (SI)	
Residual Humidity	< 0.20 %	< 0.20 %	
1.) Not for use in food contact applications			
2.) Not for use in medical or pharmaceutical applications			

Technical Data Sheet

SCHULAREC PA 66 GF 30 H

Polyamide 66



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	0.04 to 0.10 %	0.04 to 0.10 %
Suggested Max Regrind	20 %	20 %
Processing (Melt) Temp	536 to 572 °F	280 to 300 °C
Mold Temperature	140 to 248 °F	60 to 120 °C

Notes

¹ DSC

Notes

These are typical property values not to be construed as specification limits.