

Technical Data Sheet

Schulamid 66 RBL2500 BLK



Polyamide 66

Product Description

25% glass fiber reinforced PA 66, Recycled Grade

Processing Method Injection Molding

Filler/Reinforcement Glass Fiber, 25%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density, (Method A)	1.31	g/cm ³	ISO 1183
Viscosity Number	136	cm ³ /g	ISO 307
Mechanical			
Tensile Strain at Break			
(Type 1A, 5 mm/min)	2.5	%	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	7.7	%	ISO 527-2
Tensile Stress at Break			
(Type 1A, 5 mm/min)	145	MPa	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	92.0	MPa	ISO 527-2
Tensile Modulus			
(1 mm/min, Type 1A)	8000	MPa	ISO 527-1
(1 mm/min, Type 1A) - Conditioned	5200	MPa	ISO 527-1
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	7.3	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	6.3	kJ/m ²	ISO 179
(23 °C, Type 1, Edgewise, Notch A) - Conditioned	10	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	43	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise)	40	kJ/m ²	ISO 179
(23 °C, Type 1, Edgewise) - Conditioned	65	kJ/m ²	ISO 179
Thermal			
Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	>250	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	238	°C	ISO 75-2/A
Flammable			
Burning Rate			
(2.00 mm)	<100	mm/min	ISO 3795
(2.00 mm)	<100	mm/min	FMVSS 302
Injection Parameters			
Drying Time	3.0 to 4.0	hr	
Drying Temperature	80	°C	
Suggested Max Moisture	0.040 to 0.10	%	
Processing (Melt) Temp	280 to 300	°C	
Mold Temperature	60 to 120	°C	