

## Technical Data Sheet

### Schulamid B 66 GF30 NT Black



Polyamide 66

#### Product Description

Schulamid 66 GF30 B NT RBO BLK is a Polyamide 66 Glass Fiber, 30% filled material and is typically used in Injection Molding applications.

**Processing Method** Injection Molding

**Filler/Reinforcement** Glass Fiber, 30%

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Density, (Method A)	1.35	g/cm <sup>3</sup>	ISO 1183
Viscosity Number	145	cm <sup>3</sup> /g	ISO 307
<b>Mechanical</b>			
Tensile Strain at Break			
(Type 1A, 5 mm/min)	3.0	%	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	6.0	%	ISO 527-2
Tensile Stress at Break			
(Type 1A, 5 mm/min)	180	MPa	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	110	MPa	ISO 527-2
Tensile Modulus			
(1 mm/min, Type 1A)	10000	MPa	ISO 527-1
(1 mm/min, Type 1A) - Conditioned	6200	MPa	ISO 527-1
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	10	kJ/m <sup>2</sup>	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	7.0	kJ/m <sup>2</sup>	ISO 179
(23 °C, Type 1, Edgewise, Notch A) - Conditioned	18	kJ/m <sup>2</sup>	ISO 179
(-30 °C, Type 1, Edgewise, Notch A) - Conditioned	10	kJ/m <sup>2</sup>	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	80	kJ/m <sup>2</sup>	ISO 179
(-30 °C, Type 1, Edgewise)	60	kJ/m <sup>2</sup>	ISO 179
(23 °C, Type 1, Edgewise) - Conditioned	90	kJ/m <sup>2</sup>	ISO 179
(-30 °C, Type 1, Edgewise) - Conditioned	40	kJ/m <sup>2</sup>	ISO 179
Notched Izod Impact Strength			
(23 °C, Type 1, Notch A)	7.0	kJ/m <sup>2</sup>	ISO 180
(-40 °C, Type 1, Notch A)	10	kJ/m <sup>2</sup>	ISO 180
Unnotched Izod Impact Strength			
(23 °C, Type 1)	65	kJ/m <sup>2</sup>	ISO 180
(-40 °C, Type 1)	60	kJ/m <sup>2</sup>	ISO 180

**Hardness**

Ball Indentation Hardness, (H 358/30)	220	MPa	ISO 2039-1
Ball Pressure Test, (140 °C)	Pass		IEC 60695-10-2

**Thermal**

Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	250	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	250	°C	ISO 75-2/A

**Electrical**

Volume Resistivity	>1.0E+13	ohm*m	IEC 62631-3-1
- Conditioned	10000000000	ohm*m	IEC 62631-3-1
Comparative Tracking Index (CTI)	450	V	IEC 60112
Surface Resistivity	>1.0E+15	ohm	IEC 60093
- Conditioned	1000000000000	ohm	IEC 60093

**Flammable**

Burning Rate			
(2.00 mm)	30	mm/min	FMVSS 302
(2.00 mm)	30	mm/min	ISO 3795
Glow Wire Flammability Index	600	°C	IEC 60695-2-12

<b>Injection Parameters</b>	<b>Nominal Value</b>	<b>Units</b>
Drying Time	3.0 to 4.0	hr
Drying Temperature	80	°C
Suggested Max Moisture	0.040 to 0.10	%
Processing (Melt) Temp	280 to 300	°C
Mold Temperature	60 to 120	°C