

Technical Data Sheet

Vitamide AI18N 0-0063



Polyamide 66

Product Description

Vitamide AI18N 0-0063 is a Polyamide 66 material and is typically used in Injection Molding applications. Features include: High Impact Resistance.

Processing Method Injection Molding

Attribute High Impact Resistance

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density	1.11	g/cm ³	ISO 1183
Mechanical			
Tensile Stress at Yield	65	MPa	ISO 527-2
Tensile Strain at Break	40	%	ISO 527-2
Flexural Modulus	2200	MPa	ISO 178
Flexural Stress	120	MPa	ISO 178
Impact			
Notched Izod Impact Strength	15	kJ/m ²	ISO 180
Thermal			
Deflection Temperature Under Load Unannealed (0.45 MPa)	>190	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa)	>70.0	°C	ISO 75-2/A
DSC Melting Point	255	°C	ISO 3146
UL Information			
Flame Rating	HB		UL 94

Injection Parameters	Nominal Value	Units
Drying Time	3.0 to 4.0	hr
Drying Temperature	80	°C
Processing (Melt) Temp	270 to 290	°C
Mold Temperature	60 to 100	°C