

Technical Data Sheet

Purell RP271G

Polypropylene, Random Copolymer

Product Description

Purell RP271G is a low melt flow polypropylene random copolymer resin with good clarity, good impact properties, high temperature resistance suitable for autoclave sterilization. Typical customer application are medical IV solution bottles made by extrusion blow molding process.

Application Bottles For Consumer Goods; Healthcare Applications

Market Healthcare

Processing Method Extrusion Blow Molding

Attribute High Clarity; Random Copolymer

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	1.7	g/10 min	ASTM D1238
Density	0.90	g/cm ³	ASTM D792
Mechanical			
Flexural Modulus	900	MPa	ASTM D790
Tensile Strength at Yield	26	MPa	ASTM D638
Tensile Elongation at Yield	14	%	ASTM D638
Impact			
Notched Izod Impact Strength, (23 °C)	80	J/m	ASTM D256
Thermal			
Deflection Temperature Under Load, (0.46 N/mm ²)	88	°C	ASTM D648