

Technical Data Sheet

Accucomp SAN900L

Styrene Acrylonitrile
LyondellBasell Industries
Engineering Plastics

General			
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.07	1.07 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 Kg)	6.0 g/10 min	6.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	421000 psi	2900 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	9860 psi	68.0 MPa	
Break	9860 psi	68.0 MPa	
Tensile Elongation			ASTM D638
Yield	3.0 %	3.0 %	
Break	4.0 %	4.0 %	
Flexural Modulus	595000 psi	4100 MPa	ASTM D790
Flexural Strength	15500 psi	107 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (0.125 In (3.18 Mm))	0.19 ft·lb/in	10 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	124	124	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	196 °F	91.0 °C	
264 Psi (1.8 Mpa), Unannealed	174 °F	79.0 °C	

Notes

These are typical property values not to be construed as specification limits.