

Micromax™ QR150

Electronic Inks and Pastes

Gold Conductor

Micromax™ QR150 is a very high density gold conductor composition developed for fine feature screen printing and ultra fine line etching. For applications requiring high frequency or very fine conductor features, Micromax™ QR150 offers thin film performance at much lower cost.

Product benefits

- Extremely high conductivity
- Very dense fired film
- Fine line printing capability
- Excellent edge acuity when etched
- Phthalate free*

*Phthalate 'free' as used herein means that phthalate is not an intentional ingredient in and is not intentionally added to the referenced product. Trace amounts however may be present.

Product information

Solvent or thinner

Micromax™ 9450

Rheological properties

Viscosity

300 - 400^[1] Pa.s

[1]: Brookfield 2xHAT, SC4-14/6R, 10rpm, 25°C

Application technique

Mask mesh	400
Drying time	15 min
Drying temperature	150 °C
Theoretical coverage	70 - 90 ^[2] cm ² /g
Recommended film thickness, fired	5 µm
Print resolution, lines	75 ^[3] µm
Print resolution, spaces	75 ^[3] µm
Leveling time	10 - 15 min

[2]: based on fired thickness 3.5-5 μm

[3]: Line Resolution Etched

Micromax™ QR150

Electronic Inks and Pastes

Electrical properties

Surface resistivity	$\leq 5^{[4]}$ mOhm per square
---------------------	--------------------------------

[4]: @10 μ m fired

Storage and stability

Shelf life	6 ^[5] months
------------	-------------------------

[5]: in unopened containers, from date of shipment, at room temperature (<25°C)

Additional information

How to use

Processing

- **Substrates**

- Micromax™ QR150 has been successfully used on a variety of substrates including 96%, 99%, 99.6% polished alumina and thick film dielectrics including Micromax™ QM44. The properties described in this data sheet are based on test using 96% alumina substrates. Substrates of other compositions and from various manufacturers may result in variations in performance properties.

- **Printing**

- A 400-mesh stainless steel screen. Printing speeds up to 15 cm/s (6in/s) can be used.

- **Drying**

- Allow wet prints to level at room temperature, then dried.

- **Firing**

- Dried Micromax™ QR150 should be fired in a belt furnace. Use a 30 minute cycle with 850°C peak for 10 minutes.

- **Etching**

- Micromax™ QR150 may be etched in typical thin film process. Micromax™ QR150 may also be etched to achieve 3.5-5 μ m fired thickness with 2 prints, 15-20% by weight of Micromax™ 9450 is required.

Properties

- Information in this datasheet shows anticipated typical physical properties for Micromax™ QR150 based on specific controlled experiments in our labs and are not intended to represent the product specifications, details of which are available upon request.

Micromax™ QR150

Electronic Inks and Pastes

Storage and shelf life

Containers should be stored, tightly sealed, in a clean, stable environment at room temperature (<25 °C). Shelf life of material in unopened containers is six months from date of shipment. Some settling of solids may occur and compositions should be thoroughly mixed prior use.

Safety and handling

For safety and handling information pertaining to this product, read Safety Data Sheet (SDS).

Micromax™ QR150

Electronic Inks and Pastes

Adhesion wire bond after heat ageing



Printed: 2023-09-21

Page: 4 of 4

Revised: 2023-08-22 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2023 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC. KEPITAL is a registered trademark of Korea Engineering Plastics Company, Ltd.