

HDPE for Yarn

YUHWA HIDEN E308

Features
and Uses

Properties

Contact
Info.

Application	HDPE for Yarn			
Features	Good Stretch, High Tenacity			
Uses	Fishing Nets, Ropes, Insect Nets			
Items		Specification	Unit	Test Method
Melt Index		0.85	g/10min.	ASTM D1238
Density		0.956	g/cm³	ASTM D1505
Mold Shrinkage		1.5~2.5	%	KPIC Method
Water Absorption		<0.01	%	ASTM D570
Tensile Strength at Yield		250	kgf/cm²	ASTM D638
Elongation at Break		>500	%	ASTM D638
Flexural Modulus		9,000	kgf/cm²	ASTM D790
Hardness (Rockwell)		46	R Scale	ASTM D785
Impact Strength (Izod with Notch)		>50	kgf cm/cm	ASTM D256
Melting Point		134	℃	ASTM D3418
Softening Point (Vicat)		123	℃	ASTM D1525
Heat Deflection Temperature		69	℃	ASTM D648
Brittleness Temperature		<-70	℃	ASTM D746
※ Above data are intended to serve as guides only, and are not sales specification limits.				
Division	Team in charge	TEL	FAX	e-mail
International Trade	KPICC	82-2-3706-0844, 0849	82-2-3706-0893, 0894	trade@kpicc.com
Technical Service	Marketing Support Team	82-2-2122-1537	82-2-2122-1519	H15106@kpic.co.kr