



PRODUCT INFORMATION

HAIPLEN EP50 C2

Polypropylene copolymer medium flow 10% calcium carbonate filled, good surface appearance and mechanical properties.

ISO short Form ISO 1043: PP-MD10 Pellets

Key Features

- Improved impact resistance
- Mineral filled

Availability

- LP: laser printable
- L: UV stabilized
- H: heat stabilized
- D: detergent stabilized
- All colours

Process

- INJECTION MOULDING

Application

- Electronic
- Electrical
- Consumer
- Building
- Automotive

Property	Method	Unit	Value	Condition	State
PHYSICAL					
Density (+23°C)	ISO 1183	g/cm ³	0,97		
Filler content	ISO 3451	%	10	600°C - 1h	
Water Absorption (24h / +23°C)	ISO 62	%	0,05		
Mould Shrinkage (Parallel)	Internal method	%	1,2		
Mould Shrinkage (Normal)	Internal method	%	1,2		
Melt Flow Rate (MFR)	ISO 1133	g/10 min	10	230°C - 2,16 kg	
MECHANICAL					
Tensile Yield Strength	ISO 527-1,2	MPa	35	Speed 50 mm/min	
Flexural Modulus	ISO 178	MPa	1400	Speed 1 mm/min	



PRODUCT INFORMATION

HAIPLEN EP50 C2

IZOD Notched Impact	ASTM D256	J/m	90	+23°C
---------------------	-----------	-----	----	-------

THERMAL

Softening Temperature - 1 kg (VST/A/50)	ISO 306	°C	154
Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	75
Deflection Temperature 1,80 MPa (HDT A)	ISO 75A	°C	65
Coefficient of linear thermal expansion (parallel)	ISO 11359-1,-2	K ⁻¹	6X10exp(-5)

FLAMMABILITY

Flame Behaviour (1,6 mm)	UL94	Class	HB
--------------------------	------	-------	----

INJECTION MOULDING

	Value
Drying Temperature (Circulating Air Oven)	70 - 80°C
Drying Temperature (Desiccant Dryer)	70 - 80°C
Drying Time (Circulating Air Oven)	2 - 6 hours
Drying Time (Desiccant Dryer)	2 - 4 hours
Suggested Max Moisture	< 0,2 %
Suggested Max Re grind	< 15%
Melt Temperature	200 - 240°C
Feed Temperature	50°C
Rear Temperature	190°C
Middle Temperature	210°C
Front Temperature	230°C
Nozzle Temperature	220°C
Mould Temperature	30 - 50°C
Injection Rate	50 - 150 mm/sec
Injection Pressure	60 - 120 Mpa
Packing Pressure	30 - 80 Mpa
Back Pressure	Medium (0,5 - 5 MPa)
Screw Revolving Speed	50 - 150 rpm
Cushion	5 - 8 mm
Vent Depth	0,05 mm



PRODUCT INFORMATION

HAIPLLEN EP50 C2

Notes

It is normally not necessary to dry HAIPLLEN compounds, however should there be surface moisture (condensate) on the moulding compound as a result of incorrect storage, drying process is required. HAIPLLEN must be stored indoors at a temperature below 40°C avoiding humidity and direct sunlight as well. HAIPLLEN can be processed on a standard injection moulding unit. A general purpose metering screw is recommended with a zone distribution of 40% feed, 40% transition and 20% metering. When the heating cylinder is completely purged of HAIPLLEN material the machine may be shut down.