



PRODUCT INFORMATION

HAIPLEN H10 T8 HT

Polypropylene homopolymer 40% talcum filled, low flow, high stiffness and heat ageing stability.

ISO short Form ISO 1043: PP-MD40 Pellets

Key Features

- Suitable for injection moulding and extrusion applications
- Improved heat resistance

Availability

- LP: laser printable
- L: UV stabilized
- All colours

Process

- INJECTION MOULDING
- EXTRUSION

Application

- General purpose applications
- Furniture
- Building
- Automotive

Property	Method	Unit	Value	Condition	State
PHYSICAL					
Density (+23°C)	ISO 1183	g/cm ³	1,22 - 1,25		
Filler content	ISO 3451	%	40	600°C - 1h	
Water Absorption (24h / +23°C)	ISO 62	%	0,05		
Mould Shrinkage (Parallel)	Internal method	%	0,9		
Mould Shrinkage (Normal)	Internal method	%	0,9		
Melt Flow Rate (MFR)	ISO 1133	g/10 min	3	230°C - 2,16 kg	
MECHANICAL					
Tensile Yield Strength	ISO 527-1,2	MPa	35	Speed 50 mm/min	
Elongation at Break	ISO 527-1,2	%	22	Speed 50 mm/min	
Flexural Modulus	ISO 178	MPa	3800	Speed 1 mm/min	
IZOD Notched Impact	ASTM D256	J/m	25	+23°C	



PRODUCT INFORMATION

HAIPLLEN H10 T8 HT

THERMAL

Softening Temperature - 1 kg (VST/A/50)	ISO 306	°C	155	
Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	95	
Deflection Temperature 1,80 MPa (HDT A)	ISO 75A	°C	85	
Coefficient of linear thermal expansion (parallel)	ISO 11359-1,-2	K ⁻¹	6x10exp(-5)	
Heat ageing resistance	Internal method	°C	150	700 h

FLAMMABILITY

Flame Behaviour (1,6 mm)	UL94	Class	HB	
--------------------------	------	-------	----	--

EXTRUSION

	Value
Drying Time (Circulating Air Oven)	80 - 90°C
Drying Temperature (Circulating Air Oven)	3 h
Melt Temperature	190 - 210°C
Feed Temperature	160°C
Rear Temperature	170°C
Middle Temperature	180°C
Front Temperature	190°C
Die Temperature	200°C

Notes

It is normally not necessary to dry HAIPLLEN compounds, however should there be surface moisture (condensate) on the moulding compound as a result of incorrect storage, drying process is required. HAIPLLEN must be stored indoors at a temperature below 40°C avoiding humidity and direct sunlight as well. HAIPLLEN can be processed on a standard injection moulding unit. A general purpose metering screw is recommended with a zone distribution of 40% feed, 40% transition and 20% metering. When the heating cylinder is completely purged of HAIPLLEN material the machine may be shut down.



PRODUCT INFORMATION

HAIPLEN H10 T8 HT

INJECTION MOULDING	Value
Drying Temperature (Circulating Air Oven)	80 - 90°C
Drying Time (Circulating Air Oven)	2 h
Melt Temperature	200 - 210°C
Feed Temperature	160°C
Rear Temperature	170°C
Middle Temperature	190°C
Front Temperature	200°C
Nozzle Temperature	210°C
Mould Temperature	40 - 60°C
Injection Rate	MEDIUM

Notes It is normally not necessary to dry HAIPLEN compounds, however should there be surface moisture (condensate) on the moulding compound as a result of incorrect storage, drying process is required. HAIPLEN must be stored indoors at a temperature below 40°C avoiding humidity and direct sunlight as well. HAIPLEN can be processed on a standard injection moulding unit. A general purpose metering screw is recommended with a zone distribution of 40% feed, 40% transition and 20% metering. When the heating cylinder is completely purged of HAIPLEN material the machine may be shut down.