



PRODUCT INFORMATION

HAIPLEN H30 G8 BA

Polypropylene homopolymer 40% glass fibres reinforced chemically coupled, medium flow, good mechanical properties.

ISO short Form ISO 1043: PP-GF40 Pellets

Key Features

- Designed for injection moulding applications
- Glass fibres reinforced

Availability

- W: lubricated
- LP: laser printable
- L: UV stabilized
- HT: high resistance to heat
- H: heat stabilized
- FA: food approval
- D: detergent stabilized
- All colours

Process

- INJECTION MOULDING

Application

- Electrical
- Building
- Automotive

Property	Method	Unit	Value	Condition	State
PHYSICAL					
Density (+23°C)	ISO 1183	g/cm ³	1,21		
Filler content	ISO 3451	%	40	600°C - 1 h	
Water Absorption (24h / +23°C)	ISO 62	%	0,2		
Mould Shrinkage (Parallel)	Internal method	%	0,2-0,4		
Mould Shrinkage (Normal)	Internal method	%	0,6-0,8		
Melt Flow Rate (MFR)	ISO 1133	g/10 min	5	230°C - 2,16 kg	
MECHANICAL					
Elongation at Break	ISO 527-1,2	%	4	Speed 50 mm/min	



PRODUCT INFORMATION

HAIPLEN H30 G8 BA

Tensile Break Strength	ISO 527-1,2	MPa	77	Speed 50 mm/min
Flexural Modulus	ISO 178	MPa	6800	Speed 1 mm/min
Flexural Break Strength	ISO 178	MPa	80	Speed 1 mm/min
IZOD Notched Impact	ASTM D256	J/m	110	+23°C

THERMAL

Softening Temperature - 1 kg (VST/A/50)	ISO 306	°C	155
Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	140
Deflection Temperature 1,80 MPa (HDT A)	ISO 75A	°C	145

FLAMMABILITY

Flame Behaviour (1,6 mm)	UL94	Class	HB
Oxygen index	ASTM D2863	%	20

INJECTION MOULDING

	Value
Drying Temperature (Desiccant Dryer)	80 - 100°C
Drying Time (Desiccant Dryer)	2 - 4 hours
Suggested Max Moisture	0,2%
Suggested Max Re grind	< 10%
Melt Temperature	220 - 250°C
Feed Temperature	50°C
Rear Temperature	200°C
Middle Temperature	220°C
Front Temperature	230°C
Nozzle Temperature	240°C
Mould Temperature	40 - 60°C
Injection Rate	50 - 150 mm/sec
Injection Pressure	60 - 120 Mpa
Packing Pressure	30 - 80 Mpa
Back Pressure	As low as possible (<0,5 MPa)
Screw Revolving Speed	30 - 80 rpm
Cushion	5 - 8 mm
Vent Depth	0,05 mm



PRODUCT INFORMATION

HAIPLN H30 G8 BA

Notes

It is normally not necessary to dry HAIPLN compounds, however should there be surface moisture (condensate) on the moulding compound as a result of incorrect storage, drying process is required. HAIPLN must be stored indoors at a temperature below 40°C / 105°F avoiding humidity and direct sunlight as well. HAIPLN can be processed on a standard injection moulding unit. A general purpose metering screw is recommended with a zone distribution of 40% feed, 40% transition and 20% metering. When the heating cylinder is completely purged of HAIPLN material the machine may be shut down. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine or extruder size, part geometry and design.
