



PRODUCT INFORMATION

HAIPLLEN H50 C6

Polypropylene homopolymer 30% calcium carbonate filled,
medium flow.

ISO short Form ISO 1043: PP-MD30
Pellets

Key Features

- Designed for injection moulding applications
- Good flowability
- Mineral filled
- Good surface aspect

Availability

- XO: low odour emission
- W: lubricated
- LP: laser printable
- L: UV stabilized
- H: heat stabilized
- D: detergent stabilized
- All colours

Process

- INJECTION MOULDING

Application

- Electronic
- Electrical
- Consumer
- Automotive

Property	Method	Unit	Value	Condition	State
----------	--------	------	-------	-----------	-------

ELECTRICAL

Tracking Resistance (CTI - Method A)	IEC 60112	Volt	>600		
--------------------------------------	-----------	------	------	--	--

PHYSICAL

Density (+23°C)	ISO 1183	g/cm ³	1,14		
-----------------	----------	-------------------	------	--	--

Filler content	ISO 3451	%	30	550°C - 1 h	
----------------	----------	---	----	-------------	--

Granule Humidity	Internal method	%	0,05		
------------------	-----------------	---	------	--	--

Mould Shrinkage (Parallel)	Internal method	%	1,1		
----------------------------	-----------------	---	-----	--	--

Mould Shrinkage (Normal)	Internal method	%	1,1		
--------------------------	-----------------	---	-----	--	--

Melt Flow Rate (MFR)	ISO 1133	g/10 min	10	230°C - 2,16 kg	
----------------------	----------	----------	----	-----------------	--



PRODUCT INFORMATION

HAIPLEN H50 C6

MECHANICAL

Tensile Yield Strength	ISO 527-1,2	MPa	30	Speed 50 mm/min
Elongation at Break	ISO 527-1,2	%	30	Speed 50 mm/min
IZOD Notched Impact	ASTM D256	J/m	35	+23°C

THERMAL

Softening Temperature - 1 kg (VST/A/50)	ISO 306	°C	155
Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	90
Deflection Temperature 1,80 MPa (HDT A)	ISO 75A	°C	65
Deflection Temperature 0,45 MPa (HDT B)	ISO 75B	°C	125

FLAMMABILITY

Flame Behaviour (3,2 mm)	UL94	Class	HB
--------------------------	------	-------	----

INJECTION MOULDING

	Value
Drying Temperature (Desiccant Dryer)	80 - 90°C
Drying Time (Desiccant Dryer)	2 - 4 hours
Suggested Max Moisture	0,2%
Suggested Max Re grind	< 10%
Melt Temperature	190 - 220°C
Feed Temperature	160°C
Rear Temperature	180°C
Middle Temperature	190°C
Front Temperature	200°C
Nozzle Temperature	210°C
Mould Temperature	30 - 50°C
Injection Rate	50 - 150 mm/sec
Injection Pressure	60 - 120 Mpa
Packing Pressure	30 - 80 Mpa
Back Pressure	As low as possible (<0,5 MPa)
Screw Revolving Speed	30 - 80 rpm
Cushion	5 - 8 mm
Vent Depth	0,05 mm



PRODUCT INFORMATION

HAIPLLEN H50 C6

Notes

It is normally not necessary to dry HAIPLLEN compounds, however should there be surface moisture (condensate) on the moulding compound as a result of incorrect storage, drying process is required. HAIPLLEN must be stored indoors at a temperature below 40°C avoiding humidity and direct sunlight as well. HAIPLLEN can be processed on a standard injection moulding unit. A general purpose metering screw is recommended with a zone distribution of 40% feed, 40% transition and 20% metering. When the heating cylinder is completely purged of HAIPLLEN material the machine may be shut down. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine or extruder size, part geometry and design.
