



PRODUCT INFORMATION

NILENE E K20T V0 WOD

Polypropylene copolymer 20% talcum filled, medium flow, flame retardant UL94 V0, good mechanical properties.

ISO short Form ISO 1043: PP-MD20 FR(17)
UL file Pellets
E143048

Key Features

- Good impact - stiffness balance
- Designed for injection moulding applications
- Flame retardant
- Mineral filled

Availability

- YT: laser printable
- S: heat stabilized
- MT: long-term service stability for contact with copper
- L: UV stabilized
- D: detergent stabilized
- All colours

Compliance

- UL94 V0 approved all colours at 1,6 mm.

Process

- INJECTION MOULDING

Application

- Power tools
- Household
- Furniture
- Electronic
- Electrical

Property	Method	Unit	Value	Condition	State
----------	--------	------	-------	-----------	-------

ELECTRICAL

Tracking Resistance (CTI - Method A)	IEC 60112	Volt	600	UL746 A CTI class 0	
Tracking Resistance CTI	UL746 A (ASTM D3638)	PLC	0		

PHYSICAL

Density (+23°C)	ISO 1183	g/cm ³	1,34		
Filler content	ISO 3451	%	20	550°C - 1 h	
Water Absorption (24h / +23°C)	ISO 62	%	0,05		
Water Absorption at Saturation	ISO 62	%	0,1		



PRODUCT INFORMATION

NILENE E K20T V0 WOD

Mould Shrinkage (Parallel)	Internal method	%	1,1	
Mould Shrinkage (Normal)	Internal method	%	1,1	
Melt Flow Rate (MFR)	ISO 1133	g/10 min	10	230°C - 2,16 kg

MECHANICAL

Elongation at Break	ISO 527-1,2	%	>15	Speed 50 mm/min
Tensile Break Strength	ISO 527-1,2	MPa	24	Speed 50 mm/min
Flexural Modulus	ISO 178	MPa	2750	Speed 1 mm/min
IZOD Notched Impact (+23°C)	ASTM D256	J/m	50	

THERMAL

Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	75	50°C / h
Ball Pressure Test	IEC 60695-10-2	°C	125	
Continuous service temperature (20.000 h)	UL746 B	°C	110	
Continuous service temperature (short term)	UL746 B	°C	140	

FLAMMABILITY

Flame Behaviour (1,6 mm)	UL94	Class	V0	UL approved
Flame Behaviour (3,0 mm)	UL94	Class	V0	UL approved
Glow Wire Flammability Index-GWFI (1,6 mm)	IEC 60695-2-12	°C	960	
Glow Wire Ignition Temperature-GWIT (1,6 mm)	IEC 60695-2-13	°C	775	
Oxygen index	ASTM D2863	%	27	
Needle flame test (1,6 mm)	IEC 60695-11-5	-	PASSED	
Needle flame test (3,2 mm)	IEC 60695-11-5	-	PASSED	
HA1 (1,6 mm)	UL746 A	PLC	0	UL approved
HA1 (3,0 mm)	UL746 A	PLC	0	UL approved
HWI (1,6 mm)	UL746 A	PLC	3	UL approved
HWI (3,0 mm)	UL746 A	PLC	2	UL approved

INJECTION MOULDING

	Value
Drying Temperature (Circulating Air Oven)	70 - 90°C



PRODUCT INFORMATION

NILENE E K20T V0 WOD

Drying Temperature (Desiccant Dryer)	70 - 90°C
Drying Time (Circulating Air Oven)	3 - 5 hours
Drying Time (Desiccant Dryer)	0,5 - 2,5 hours
Suggested Max Moisture	0,2%
Suggested Max Re grind	< 5%
Melt Temperature	190 - 210°C
Feed Temperature	50°C
Rear Temperature	170°C
Middle Temperature	180°C
Front Temperature	190°C
Nozzle Temperature	200°C
Mould Temperature	40 - 60°C
Injection Rate	50 - 150 mm/sec
Back Pressure	0,3 - 0,5 Mpa
Screw Revolving Speed	50 - 100 rpm
Cushion	3 - 6 mm
Vent Depth	0,05 mm

Notes It is normally not necessary to dry NILENE compounds, however should there be surface moisture (condensate) on the moulding compound as a result of incorrect storage, drying process is required. NILENE must be stored indoors at a temperature below 40°C avoiding humidity and direct sunlight as well. NILENE can be processed on a standard injection moulding unit. A general purpose metering screw is recommended with a zone distribution of 40% feed, 40% transition and 20% metering. When the heating cylinder is completely purged of NILENE material the machine may be shut down.