



PRODUCT INFORMATION

NILENE E15 K15TE

Polypropylene copolymer 15% mineral filled, medium high flow, designed for aesthetical applications.

ISO short Form ISO 1043: PP-MD15 Pellets

Key Features

- Good impact - stiffness balance
- Good flowability
- Mineral filled
- Good surface aspect

Availability

- YT: laser printable
- S: heat stabilized
- AT: antistatic
- L: UV stabilized
- D: detergent stabilized
- All colours

Process

- INJECTION MOULDING

Application

- Electrical
- Consumer
- Automotive

Property	Method	Unit	Value	Condition	State
PHYSICAL					
Density (+23°C)	ISO 1183	g/cm ³	1,01		
Filler content	ISO 3451	%	15	600°C - 1h	
Water Absorption (24h / +23°C)	ISO 62	%	0,04		
Mould Shrinkage (Parallel)	Internal method	%	1,2 - 1,4		
Mould Shrinkage (Normal)	Internal method	%	1,2 - 1,4		
Melt Flow Rate (MFR)	ISO 1133	g/10 min	15	230°C - 2,16 kg	
MECHANICAL					
Tensile Modulus	ISO 527-1,2	MPa	1800	Speed 1 mm/min	
Tensile Yield Strength	ISO 527-1,2	MPa	22	Speed 50 mm/min	
Elongation at Break	ISO 527-1,2	%	35	Speed 50 mm/min	



PRODUCT INFORMATION

NILENE E15 K15TE

Flexural Modulus	ISO 178	MPa	1600	Speed 1 mm/min
IZOD Notched Impact	ASTM D256	J/m	60	+23°C

THERMAL

Softening Temperature - 1 kg (VST/A/50)	ISO 306	°C	145
Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	75
Deflection Temperature 1,80 MPa (HDT A)	ISO 75A	°C	55
Deflection Temperature 0,45 MPa (HDT B)	ISO 75B	°C	125
Coefficient of linear thermal expansion (parallel)	ISO 11359-1,-2	K ⁻¹	6x10exp(-5)

FLAMMABILITY

Flame Behaviour (1,6 mm)	UL94	Class	HB
--------------------------	------	-------	----

INJECTION MOULDING	Value
Drying Temperature (Circulating Air Oven)	70 - 90°C
Drying Temperature (Desiccant Dryer)	70 - 90°C
Drying Time (Circulating Air Oven)	3 - 5 hours
Drying Time (Desiccant Dryer)	0,5 - 2,5 hours
Suggested Max Moisture	0,2%
Suggested Max Re grind	< 5%
Melt Temperature	190 - 210°C
Feed Temperature	50°C
Rear Temperature	170°C
Middle Temperature	180°C
Front Temperature	190°C
Nozzle Temperature	200°C
Mould Temperature	40 - 60°C
Injection Rate	50 - 150 mm/sec
Back Pressure	0,3 - 0,5 Mpa
Screw Revolving Speed	50 - 100 rpm
Cushion	3 - 6 mm
Vent Depth	0,05 mm



PRODUCT INFORMATION

NILENE E15 K15TE

Notes It is normally not necessary to dry NILENE compounds, however should there be surface moisture (condensate) on the moulding compound as a result of incorrect storage, drying process is required. NILENE must be stored indoors at a temperature below 40°C avoiding humidity and direct sunlight as well. NILENE can be processed on a standard injection moulding unit. A general purpose metering screw is recommended with a zone distribution of 40% feed, 40% transition and 20% metering. When the heating cylinder is completely purged of NILENE material the machine may be shut down.