



PRODUCT INFORMATION

NILENE E20 K25T

Polypropylene copolymer 25% talcum filled, high flow.

ISO short Form ISO 1043: PP-MD25
Pellets

Key Features

- Good impact - stiffness balance
- High flow
- Mineral filled

Availability

- YT: laser printable
- S: heat stabilized
- AT: antistatic
- L: UV stabilized
- All colours

Process

- INJECTION MOULDING

Application

- Electrical
- Consumer
- Automotive

Property	Method	Unit	Value	Condition	State
----------	--------	------	-------	-----------	-------

ELECTRICAL

Tracking Resistance (CTI - Method A)	IEC 60112	Volt	>600		
--------------------------------------	-----------	------	------	--	--

PHYSICAL

Density (+23°C)	ISO 1183	g/cm ³	1,09-1,11		
-----------------	----------	-------------------	-----------	--	--

Filler content	ISO 3451	%	25	600°C - 1 h	
----------------	----------	---	----	-------------	--

Water Absorption (24h / +23°C)	ISO 62	%	0,05		
--------------------------------	--------	---	------	--	--

Mould Shrinkage (Parallel)	Internal method	%	1,1		
----------------------------	-----------------	---	-----	--	--

Mould Shrinkage (Normal)	Internal method	%	1,1		
--------------------------	-----------------	---	-----	--	--

Melt Flow Rate (MFR)	ISO 1133	g/10 min	20	230°C - 2,16 kg	
----------------------	----------	----------	----	-----------------	--

MECHANICAL

Tensile Yield Strength	ISO 527-1,2	MPa	30	Speed 50 mm/min	
------------------------	-------------	-----	----	-----------------	--

Elongation at Break	ISO 527-1,2	%	25	Speed 50 mm/min	
---------------------	-------------	---	----	-----------------	--



PRODUCT INFORMATION

NILENE E20 K25T

Flexural Modulus	ISO 178	MPa	2300	Speed 1 mm/min
IZOD Notched Impact	ASTM D256	J/m	60	+23°C
IZOD Notched Impact	ASTM D256	J/m	40	+0°C
IZOD Notched Impact	ASTM D256	J/m	25	-20°C
CHARPY Notched Impact (+23°C)	ISO 179/1eA	kJ/m ²	5	

THERMAL

Softening Temperature - 1 kg (VST/A/50)	ISO 306	°C	152	
Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	80	
Deflection Temperature 1,80 MPa (HDT A)	ISO 75A	°C	65	
Deflection Temperature 0,45 MPa (HDT B)	ISO 75B	°C	135	
Coefficient of linear thermal expansion (parallel)	ISO 11359-1,-2	K ⁻¹	6x10exp(-5)	

FLAMMABILITY

Flame Behaviour (1,6 mm)	UL94	Class	HB	
Glow Wire Flammability Index-GWFI (1,6 mm)	IEC 60695-2-12	°C	650	
Burning Rate (US-FMVSS 302)	ISO 3795	mm/min	<100	Thickness 2 mm

INJECTION MOULDING

	Value
Drying Temperature (Circulating Air Oven)	70 - 90°C
Drying Temperature (Desiccant Dryer)	70 - 90°C
Drying Time (Circulating Air Oven)	3 - 5 hours
Drying Time (Desiccant Dryer)	0,5 - 2,5 hours
Suggested Max Moisture	0,2%
Suggested Max Re grind	< 5%
Melt Temperature	190 - 210°C
Feed Temperature	50°C
Rear Temperature	170°C
Middle Temperature	180°C
Front Temperature	190°C
Nozzle Temperature	200°C
Mould Temperature	40 - 60°C



PRODUCT INFORMATION

NILENE E20 K25T

Injection Rate	50 - 150 mm/sec
Back Pressure	0,3 - 0,5 Mpa
Screw Revolving Speed	50 - 100 rpm
Cushion	3 - 6 mm
Vent Depth	0,05 mm

Notes It is normally not necessary to dry NILENE compounds, however should there be surface moisture (condensate) on the moulding compound as a result of incorrect storage, drying process is required. NILENE must be stored indoors at a temperature below 40°C avoiding humidity and direct sunlight as well. NILENE can be processed on a standard injection moulding unit. A general purpose metering screw is recommended with a zone distribution of 40% feed, 40% transition and 20% metering. When the heating cylinder is completely purged of NILENE material the machine may be shut down.