



PRODUCT INFORMATION

NILENE E6 K20VA V0

Polypropylene copolymer medium flow 20% glass fibres reinforced chemically coupled, flame retardant UL94 V0, good mechanical properties.

ISO short Form ISO 1043: PP-GF20 FR(17)
Pellets

Key Features

- Glass fibres reinforced
- Flame retardant

Availability

- YT: laser printable
- S: heat stabilized
- MT: long-term service stability for contact with copper
- L: UV stabilized
- D: detergent stabilized
- All colours

Process

- INJECTION MOULDING

Application

- Power tools
- Household
- Electronic
- Electrical

Property	Method	Unit	Value	Condition	State
----------	--------	------	-------	-----------	-------

PHYSICAL

Density (+23°C)	ISO 1183	g/cm ³	1,36		
Filler content	ISO 3451	%	20		
Mould Shrinkage (Parallel)	Internal method	%	0,30 - 0,50		
Mould Shrinkage (Normal)	Internal method	%	0,45 - 0,65		
Melt Flow Rate (MFR)	ISO 1133	g/10 min	6	230°C - 2,16 kg	

MECHANICAL

Tensile Modulus	ISO 527-1,2	MPa	4600		
Elongation at Break	ISO 527-1,2	%	4	Speed 50 mm/min	



PRODUCT INFORMATION

NILENE E6 K20VA V0

Tensile Break Strength	ISO 527-1,2	MPa	45	Speed 50 mm/min
Flexural Modulus	ISO 178	MPa	4000	Speed 1 mm/min
IZOD Notched Impact (+23°C)	ASTM D256	J/m	60	

THERMAL

Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	102	50°C / h
Deflection Temperature 1,80 MPa (HDT A)	ISO 75A	°C	120	120°C / h
Ball Pressure Test	IEC 60695-10-2	°C	100	
Continuous service temperature (20.000 h)	UL746 B	°C	80	
Coefficient of linear thermal expansion (parallel)	ISO 11359-1,-2	K ⁻¹	7x10exp(-5)	

FLAMMABILITY

Flame Behaviour (1,6 mm)	UL94	Class	V0
Flame Behaviour (3,2 mm)	UL94	Class	V0
Glow Wire Flammability Index-GWFI (1,6 mm)	IEC 60695-2-12	°C	960
Glow Wire Ignition Temperature-GWIT (1,6 mm)	IEC 60695-2-13	°C	775

INJECTION MOULDING

	Value
Drying Temperature (Desiccant Dryer)	70 - 80°C
Drying Time (Desiccant Dryer)	2 - 4 hours
Suggested Max Moisture	0,2%
Suggested Max Regrind	< 10%
Melt Temperature	180 - 220°C
Feed Temperature	150°C
Rear Temperature	170°C
Middle Temperature	190°C
Front Temperature	200°C
Nozzle Temperature	210°C
Mould Temperature	30 - 70°C
Injection Rate	Slow to Medium
Injection Pressure	80 - 120 Mpa
Packing Pressure	60 - 100 Mpa



PRODUCT INFORMATION

NILENE E6 K20VA V0

Back Pressure	5 - 10 Mpa
Screw Revolving Speed	< 300 mm/sec
Cushion	< 5 mm
Vent Depth	0,05 mm

Notes It is normally not necessary to dry NILENE compounds, however should there be surface moisture (condensate) on the moulding compound as a result of incorrect storage, drying process is required. NILENE must be stored indoors at a temperature below 40°C avoiding humidity and direct sunlight as well. NILENE can be processed on a standard injection moulding unit. A general purpose metering screw is recommended with a zone distribution of 40% feed, 40% transition and 20% metering. When the heating cylinder is completely purged of NILENE material the machine may be shut down.