



PRODUCT INFORMATION

**NILENE P K10T**

Polypropylene homopolymer 10% talcum filled flame rating UL94 HB.

**ISO short** ISO 1043: PP-MD10  
**Form** Pellets  
**UL file** E143048

**Key Features**

- Designed for injection moulding applications
- Good flowability
- Mineral filled

**Availability**

- YT: laser printable
- S: heat stabilized
- AT: antistatic
- L: UV stabilized
- D: detergent stabilized
- All colours

**Compliance**

- UL94 HB approved all colours at 1,6 mm. UL746 B approved.

**Process**

- INJECTION MOULDING

**Application**

- Household
- Electronic
- Electrical
- Automotive

Property	Method	Unit	Value	Condition	State
----------	--------	------	-------	-----------	-------

**ELECTRICAL**

Tracking Resistance (CTI - Method A)	IEC 60112	Volt	600		
--------------------------------------	-----------	------	-----	--	--

**PHYSICAL**

Density (+23°C)	ISO 1183	g/cm <sup>3</sup>	0,97		
Filler content	ISO 3451	%	10	600°C - 1h	
Water Absorption (24h / +23°C)	ISO 62	%	0,05		
Mould Shrinkage (Parallel)	Internal method	%	1,3		
Mould Shrinkage (Normal)	Internal method	%	1,3		
Melt Flow Rate (MFR)	ISO 1133	g/10 min	15	230°C - 2,16 kg	



PRODUCT INFORMATION

**NILENE P K10T**

**MECHANICAL**

Tensile Modulus	ISO 527-1,2	MPa	2300	Speed 1 mm/min
Tensile Yield Strength	ISO 527-1,2	MPa	30	Speed 50 mm/min
Elongation at Break	ISO 527-1,2	%	40	Speed 50 mm/min
Flexural Modulus	ISO 178	MPa	2200	Speed 1 mm/min
Flexural Max Strength	ISO 178	MPa	45	Speed 1 mm/min
IZOD Notched Impact	ASTM D256	J/m	20	-20°C
IZOD Notched Impact	ASTM D256	J/m	40	+23°C
CHARPY Notched Impact (+23°C)	ISO 179/1eA	kJ/m <sup>2</sup>	3,5	

**THERMAL**

Softening Temperature - 1 kg (VST/A/50)	ISO 306	°C	155	
Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	85	
Deflection Temperature 1,80 MPa (HDT A)	ISO 75A	°C	68	
Coefficient of linear thermal expansion (parallel)	ISO 11359-1,-2	K <sup>-1</sup>	6X10exp(-5)	

**FLAMMABILITY**

Flame Behaviour (1,6 mm)	UL94	Class	HB	UL approved
Glow Wire Flammability Index-GWFI (1,6 mm)	IEC 60695-2-12	°C	650	
Glow Wire Ignition Temperature-GWIT (1,6 mm)	IEC 60695-2-13	°C	550	
Oxygen index	ASTM D2863	%	21	

**INJECTION MOULDING**

	Value
Drying Temperature (Circulating Air Oven)	70 - 90°C
Drying Temperature (Desiccant Dryer)	70 - 90°C
Drying Time (Circulating Air Oven)	3 - 5 hours
Drying Time (Desiccant Dryer)	0,5 - 2,5 hours
Suggested Max Moisture	0,2%
Suggested Max Re grind	< 10%
Melt Temperature	190 - 230°C
Feed Temperature	50°C



PRODUCT INFORMATION

**NILENE P K10T**

Rear Temperature	170°C
Middle Temperature	190°C
Front Temperature	200°C
Nozzle Temperature	220°C
Mould Temperature	40 - 60°C
Injection Rate	50 - 150 mm/sec
Back Pressure	0,3 - 0,5 Mpa
Screw Revolving Speed	50 - 100 rpm
Cushion	3 - 6 mm
Vent Depth	0,05 mm

**Notes** It is normally not necessary to dry NILENE compounds, however should there be surface moisture (condensate) on the moulding compound as a result of incorrect storage, drying process is required. NILENE must be stored indoors at a temperature below 40°C avoiding humidity and direct sunlight as well. NILENE can be processed on a standard injection moulding unit. A general purpose metering screw is recommended with a zone distribution of 40% feed, 40% transition and 20% metering. When the heating cylinder is completely purged of NILENE material the machine may be shut down.