



PRODUCT INFORMATION

NILENE P3 K20VA

Polypropylene homopolymer 20% glass fibres reinforced chemically coupled, low flow, good mechanical properties.

ISO short Form ISO 1043: PP-GF20 Pellets

Key Features

- Designed for injection moulding applications
- Glass fibres reinforced
- Low flow

Availability

- YT: laser printable
- S: heat stabilized
- AT: antistatic
- L: UV stabilized
- D: detergent stabilized
- All colours

Process

- INJECTION MOULDING

Application

- General purpose applications

Property	Method	Unit	Value	Condition	State
PHYSICAL					
Density (+23°C)	ISO 1183	g/cm ³	1,05		
Filler content	ISO 3451	%	20	600°C - 1 h	
Water Absorption (24h / +23°C)	ISO 62	%	0,05		
Mould Shrinkage (Parallel)	Internal method	%	0,35 - 0,65		
Mould Shrinkage (Normal)	Internal method	%	0,85 - 0,95		
Melt Flow Rate (MFR)	ISO 1133	g/10 min	3	230°C - 2,16 kg	
MECHANICAL					
Elongation at Break	ISO 527-1,2	%	10	Speed 50 mm/min	
Tensile Break Strength	ISO 527-1,2	MPa	50	Speed 1 mm/min	
Flexural Modulus	ISO 178	MPa	4500	Speed 1 mm/min	
IZOD Notched Impact	ASTM D256	J/m	90	+23°C	

THERMAL



PRODUCT INFORMATION

NILENE P3 K20VA

Softening Temperature - 1 kg (VST/A/50)	ISO 306	°C	155
Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	135
Deflection Temperature 1,80 MPa (HDT A)	ISO 75A	°C	130
Deflection Temperature 0,45 MPa (HDT B)	ISO 75B	°C	142

FLAMMABILITY

Flame Behaviour (1,6 mm)	UL94	Class	HB
Burning Rate (US-FMVSS 302)	ISO 3795	mm/min	< 100 Thickness 2 mm
Oxygen index	ASTM D2863	%	21

INJECTION MOULDING

	Value
Drying Temperature (Circulating Air Oven)	80 - 100°C
Drying Temperature (Desiccant Dryer)	80 - 100°C
Drying Time (Circulating Air Oven)	3 - 6 hours
Drying Time (Desiccant Dryer)	2 - 4 hours
Suggested Max Moisture	0,2%
Suggested Max Re grind	< 10%
Melt Temperature	220 - 250°C
Feed Temperature	50°C
Rear Temperature	200°C
Middle Temperature	220°C
Front Temperature	230°C
Nozzle Temperature	240°C
Mould Temperature	40 - 60°C
Injection Rate	50 - 150 mm/sec
Injection Pressure	60 - 120 Mpa
Packing Pressure	30 - 80 Mpa
Back Pressure	As low as possible (<0,5 MPa)
Screw Revolving Speed	30 - 80 rpm
Cushion	5 - 8 mm
Vent Depth	0,05 mm



PRODUCT INFORMATION

NILENE P3 K20VA

Notes It is normally not necessary to dry NILENE compounds, however should there be surface moisture (condensate) on the moulding compound as a result of incorrect storage, drying process is required. NILENE must be stored indoors at a temperature below 40°C avoiding humidity and direct sunlight as well. NILENE can be processed on a standard injection moulding unit. A general purpose metering screw is recommended with a zone distribution of 40% feed, 40% transition and 20% metering. When the heating cylinder is completely purged of NILENE material the machine may be shut down.
