

Processing Guidelines

Pro-Touch™ 8690- (Any Color)

Pressures

Injection	600 - 1400 psi
Holding	150 - 900 psi
Back	075 - 125 psi

Injection Speed

2.0 - 5.0 in/s

Temperatures

• Barrel Zone 1	400-440 °F
• Barrel Zone 2	400-440 °F
• Barrel Zone 3	410-450 °F
• Barrel Zone 4	410-450 °F
• Nozzle	420-460 °F
• Hot Runner	420-460 °F
• Mold	80-160 °F
• Hydraulic Oil Temperature	110-125 °F

Material Drying is typically not required but for some thin walled parts drying may be required. If needed dry at 160 – 190°F for 1-2 hours.

Machine/Shot Information

Shot Capacity vs. Barrel Capacity	2.5 to 4.0
Cushion	1/8" to 1/4"
Screw Decompression	0.10" to 0.25"
Clamp Tonnage should be 2.5 to 4.0 Tons per square inch of projected part area.	