



PRODUCT INFORMATION

TAROLOX 10 G2 X0

PBT medium viscosity 10% glass fibres reinforced, flame retardant UL94 V0, good flow, good surface appearance, good mechanical properties, high dimensional stability.

ISO short Form ISO 1043: PBT-GF10 FR(17)
UL file Pellets
 E143048

Key Features

- Designed for injection moulding applications
- Glass fibres reinforced
- Flame retardant
- Good flowability
- Good dimensional stability

Availability

- W: lubricated
- LP: laser printable
- L: UV stabilized
- H: heat stabilized
- All colours

Compliance

- UL94 V0 approved all colours at 0,97 mm. UL746 B approved.

Process

- INJECTION MOULDING

Application

- Power tools
- Electronic
- Electrical
- Connectors
- Building
- Automotive

Property	Method	Unit	Value	Condition	State
ELECTRICAL					
Volume Resistivity	IEC 60093	Ohm cm	> 10E15		
Dielectric Strength	IEC 60243-1	kV/mm	20	2 mm	
Dissipation Factor Frequency	IEC 60250	-	0,020	1 MHz	
Dielectric Constant	IEC 60250	-	3,2	1 MHz	
Tracking Resistance (CTI - Method A)	IEC 60112	Volt	250		
Tracking Resistance (CTI - Method B)	IEC 60112	Volt	175M		
PHYSICAL					
Density (+23°C)	ISO 1183	g/cm ³	1,48		

PRODUCT INFORMATION

TAROLOX 10 G2 X0

Filler content	ISO 3451	%	10	850°C - 1 h
Granule Humidity	Internal method	%	< 0,05	
Water Absorption (24h / +23°C)	ISO 62	%	0,05	
Water Absorption at Saturation	ISO 62	%	0,32	
Mould Shrinkage (Parallel)	Internal method	%	0,6 - 1,0	
Mould Shrinkage (Normal)	Internal method	%	0,9 - 1,3	
Melting temperature (DSC)	ISO 11357	°C	225	

MECHANICAL

Tensile Modulus	ISO 527-1,2	MPa	5000	Speed 1 mm/min
Elongation at Break	ISO 527-1,2	%	6	Speed 50 mm/min
Tensile Break Strength	ISO 527-1,2	MPa	85	Speed 50 mm/min
Flexural Modulus	ISO 178	MPa	4500	Speed 1 mm/min
Flexural Break Strength	ISO 178	MPa	110	Speed 1 mm/min
IZOD Notched Impact (+23°C)	ASTM D256	J/m	50	
CHARPY Notched Impact (+23°C)	ISO 179/1eA	kJ/m ²	4	

THERMAL

Softening Temperature - 1 kg (VST/A/50)	ISO 306	°C	210	50°C / h
Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	205	50°C / h
Deflection Temperature 1,80 MPa (HDT A)	ISO 75A	°C	180	120°C / h
Deflection Temperature 0,45 MPa (HDT B)	ISO 75B	°C	206	120°C / h
Ball Pressure Test	IEC 60695-10-2	°C	185	
Continuous service temperature (20.000 h)	UL746 B	°C	90 (120 H)	
Continuous service temperature (short term)	UL746 B	°C	130 (160 H)	
Coefficient of linear thermal expansion (parallel)	ISO 11359-1,-2	K ⁻¹	3x10E(-5)	-30°C / +30°C

FLAMMABILITY

Flame Behaviour (0,75 mm)	UL94	Class	V0	
Flame Behaviour (0,97 mm)	UL94	Class	V0	UL approved

PRODUCT INFORMATION

TAROLOX 10 G2 X0

Flame Behaviour (1,6 mm)	UL94	Class	V0
Flame Behaviour (3,2 mm)	UL94	Class	V0
Glow Wire Flammability Index-GWFI (2 mm)	IEC 60695-2-12	°C	960
Oxygen index	ASTM D2863	%	29

INJECTION MOULDING	Value
Drying Temperature (Circulating Air Oven)	80 - 120°C
Drying Temperature (Desiccant Dryer)	80 - 120°C
Drying Time (Circulating Air Oven)	3 - 6 h
Drying Time (Desiccant Dryer)	2 - 4 h
Suggested Max Moisture	< 0,04 %
Suggested Max Re grind	< 20%
Melt Temperature	250 - 270°C
Feed Temperature	60°C
Rear Temperature	235°C
Middle Temperature	245°C
Front Temperature	255°C
Nozzle Temperature	260°C
Mould Temperature	60 - 100°C
Injection Rate	Medium to Fast
Injection Pressure	40 - 100 Mpa
Packing Pressure	30 - 80 Mpa
Back Pressure	0,5 - 1 Mpa
Screw Revolving Speed	70 rpm @ Diameter 60 mm
Screw Revolving Speed	95 rpm @ Diameter 45 mm
Screw Revolving Speed	140 rpm @ Diameter 30 mm
Screw Revolving Speed	220 rpm @ Diameter 20 mm
Screw Revolving Speed	300 rpm @ Diameter 15 mm
Cushion	2 - 6 mm
Screw L/D Ratio	18 - 22
Screw Compression Ratio	2:1 - 2,5:1
Vent Depth	0,02 mm

Notes During processing, a dehumidifying hopper dryer is recommended at a temperature of 60 to 80°C.