



PRODUCT INFORMATION

TAROLOX 111 G5

PET medium viscosity 25% glass fibres reinforced, very good chemical resistance, good mechanical, thermal and electrical properties, low moisture absorption, good dimensional stability.

ISO short Form ISO 1043: PET-GF25 Pellets

Key Features

- Good impact - stiffness balance
- High stiffness
- Designed for injection moulding applications
- Glass fibres reinforced
- Excellent filling qualities
- Excellent surface smoothness
- Good surface aspect

Availability

- W: lubricated
- LP: laser printable
- L: UV stabilized
- H: heat stabilized
- All colours

Process

- INJECTION MOULDING

Application

- Electrical
- Automotive

Property	Method	Unit	Value	Condition	State
----------	--------	------	-------	-----------	-------

ELECTRICAL

Dielectric Strength	IEC 60243-1	kV/mm	34	1 mm	
Dissipation Factor Frequency	IEC 60250	-	0,02		
Tracking Resistance (CTI - Method A)	IEC 60112	Volt	250		

PHYSICAL

Density (+23°C)	ISO 1183	g/cm ³	1,51-1,53		
Filler content	ISO 3451	%	25	750°C - 1 h	
Granule Humidity	Internal method	%	<0,02		
Water Absorption (24h / +23°C)	ISO 62	%	0,06		
Mould Shrinkage (Parallel)	Internal method	%	0,25 - 0,4		
Mould Shrinkage (Normal)	Internal method	%	0,4 - 0,7		



PRODUCT INFORMATION

TAROLOX 111 G5

Melting temperature (DSC)	ISO 11357	°C	256
---------------------------	-----------	----	-----

MECHANICAL

Tensile Modulus	ISO 527-1,2	MPa	8500	Speed 1 mm/min
Elongation at Break	ISO 527-1,2	%	2,2	Speed 50 mm/min
Tensile Break Strength	ISO 527-1,2	MPa	125	Speed 50 mm/min
Flexural Modulus	ISO 178	MPa	7800	Speed 1 mm/min
Flexural Break Strength	ISO 178	MPa	185	Speed 1 mm/min
IZOD Notched Impact	ASTM D256	J/m	75	+23°C
IZOD Notched Impact	ASTM D256	J/m	55	-20°C
CHARPY Notched Impact (+23°C)	ISO 179/1eA	kJ/m ²	9	
CHARPY Unnotched Impact (+23°C)	ISO 179/1eU	kJ/m ²	45	

THERMAL

Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	230	50°C / h
Deflection Temperature 1,80 MPa (HDT A)	ISO 75A	°C	225	120°C / h
Ball Pressure Test	IEC 60695-10-2	°C	245	
Coefficient of linear thermal expansion (parallel)	ISO 11359-1,-2	K ⁻¹	3,5x10exp(-5)	-30°C /+30°C

FLAMMABILITY

Flame Behaviour (0,97 mm)	UL94	Class	HB
Glow Wire Flammability Index-GWFI (2 mm)	IEC 60695-2-12	°C	750
Oxygen index	ASTM D2863	%	24

INJECTION MOULDING

	Value
Drying Temperature (Desiccant Dryer)	80 - 120°C
Drying Time (Desiccant Dryer)	2 - 4 h
Suggested Max Moisture	< 0,03
Suggested Max Regrind	< 10%
Melt Temperature	260 - 285°C
Feed Temperature	250°C
Rear Temperature	265°C



PRODUCT INFORMATION

TAROLOX 111 G5

Middle Temperature	270°C
Front Temperature	275°C
Nozzle Temperature	275°C
Mould Temperature	60 - 100°C
Injection Rate	Medium to Fast
Injection Pressure	40 - 100 Mpa
Packing Pressure	30 - 80 Mpa
Back Pressure	0,5 - 1 Mpa
Screw Revolving Speed	70 rpm @ Diameter 60 mm
Screw Revolving Speed	95 rpm @ Diameter 45 mm
Screw Revolving Speed	140 rpm @ Diameter 30 mm
Screw Revolving Speed	220 rpm @ Diameter 20 mm
Cushion	2 - 6 mm
Screw L/D Ratio	18 - 22
Screw Compression Ratio	2:1 - 2,5:1
Vent Depth	0,02 mm

Notes During processing, a dehumidifying hopper dryer is recommended at a temperature of 60 to 80°C.