



PRODUCT INFORMATION

TAROLOX 111 G6

PET medium viscosity 30% glass fibres reinforced, very good chemical resistance, good mechanical, thermal and electrical properties, low moisture absorption, good dimensional stability.

ISO short Form ISO 1043: PET-GF30 Pellets

Key Features

- Good impact - stiffness balance
- High stiffness
- Designed for injection moulding applications
- Glass fibres reinforced
- Excellent filling qualities
- Excellent surface smoothness
- Good surface aspect

Availability

- W: lubricated
- LP: laser printable
- L: UV stabilized
- H: heat stabilized
- All colours

Process

- INJECTION MOULDING

Application

- Electrical
- Automotive

| Property | Method | Unit | Value | Condition | State |
|----------|--------|------|-------|-----------|-------|
|----------|--------|------|-------|-----------|-------|

ELECTRICAL

| | | | | | |
|--------------------------------------|-------------|--------|-----------|------|--|
| Volume Resistivity | IEC 60093 | Ohm cm | 10exp(15) | | |
| Dielectric Strength | IEC 60243-1 | kV/mm | 34 | 1 mm | |
| Dissipation Factor Frequency | IEC 60250 | - | 0,012 | | |
| Dielectric Constant | IEC 60250 | - | 3,6 | | |
| Tracking Resistance (CTI - Method A) | IEC 60112 | Volt | 250 | | |

PHYSICAL

| | | | | | |
|--------------------------------|-----------------|-------------------|-----------|-------------|--|
| Density (+23°C) | ISO 1183 | g/cm ³ | 1,55-1,57 | | |
| Filler content | ISO 3451 | % | 30 | 750°C - 1 h | |
| Granule Humidity | Internal method | % | <0,03 | | |
| Water Absorption (24h / +23°C) | ISO 62 | % | 0,05 | | |



PRODUCT INFORMATION

TAROLOX 111 G6

| | | | |
|----------------------------|-----------------|----|-----------|
| Mould Shrinkage (Parallel) | Internal method | % | 0,2-0,3 |
| Mould Shrinkage (Normal) | Internal method | % | 0,5 - 0,7 |
| Melting temperature (DSC) | ISO 11357 | °C | 256 |

MECHANICAL

| | | | | |
|---------------------------------|-------------|-------------------|-------|-----------------|
| Tensile Modulus | ISO 527-1,2 | MPa | 10000 | Speed 1 mm/min |
| Elongation at Break | ISO 527-1,2 | % | 2,5 | Speed 50 mm/min |
| Tensile Break Strength | ISO 527-1,2 | MPa | 135 | Speed 50 mm/min |
| Flexural Modulus | ISO 178 | MPa | 9000 | Speed 1 mm/min |
| Flexural Break Strength | ISO 178 | MPa | 220 | Speed 1 mm/min |
| IZOD Notched Impact | ASTM D256 | J/m | 70 | -20°C |
| IZOD Notched Impact | ASTM D256 | J/m | 85 | +23°C |
| CHARPY Notched Impact (+23°C) | ISO 179/1eA | kJ/m ² | 9 | |
| CHARPY Unnotched Impact (+23°C) | ISO 179/1eU | kJ/m ² | 46 | |

THERMAL

| | | | | |
|--|----------------|-----------------|-------------|--------------|
| Softening Temperature - 5 kg (VST/B/50) | ISO 306 | °C | 240 | 50°C / h |
| Deflection Temperature 1,80 MPa (HDT A) | ISO 75A | °C | 225 | 120°C / h |
| Deflection Temperature 0,45 MPa (HDT B) | ISO 75B | °C | 246 | 120°C / h |
| Ball Pressure Test | IEC 60695-10-2 | °C | 245 | |
| Continuous service temperature (20.000 h) | UL746 B | °C | 140 | |
| Continuous service temperature | UL746 B | °C | 140 | |
| Coefficient of linear thermal expansion (parallel) | ISO 11359-1,-2 | K ⁻¹ | 3x10exp(-5) | -30°C /+30°C |

FLAMMABILITY

| | | | |
|--|----------------|-------|-----|
| Flame Behaviour (0,97 mm) | UL94 | Class | HB |
| Flame Behaviour (1,6 mm) | UL94 | Class | HB |
| Glow Wire Flammability Index-GWFI (2 mm) | IEC 60695-2-12 | °C | 750 |
| Oxygen index | ASTM D2863 | % | 24 |



PRODUCT INFORMATION

TAROLOX 111 G6

| INJECTION MOULDING | Value |
|--------------------------------------|--------------------------|
| Drying Temperature (Desiccant Dryer) | 80 - 120°C |
| Drying Time (Desiccant Dryer) | 2 - 4 h |
| Suggested Max Moisture | < 0,03 |
| Suggested Max Re grind | < 10% |
| Melt Temperature | 260 - 285°C |
| Feed Temperature | 250°C |
| Rear Temperature | 265°C |
| Middle Temperature | 270°C |
| Front Temperature | 275°C |
| Nozzle Temperature | 275°C |
| Mould Temperature | 60 - 100°C |
| Injection Rate | Medium to Fast |
| Injection Pressure | 40 - 100 Mpa |
| Packing Pressure | 30 - 80 Mpa |
| Back Pressure | 0,5 - 1 Mpa |
| Screw Revolving Speed | 70 rpm @ Diameter 60 mm |
| Screw Revolving Speed | 95 rpm @ Diameter 45 mm |
| Screw Revolving Speed | 140 rpm @ Diameter 30 mm |
| Screw Revolving Speed | 220 rpm @ Diameter 20 mm |
| Cushion | 2 - 6 mm |
| Screw L/D Ratio | 18 - 22 |
| Screw Compression Ratio | 2:1 - 2,5:1 |
| Vent Depth | 0,02 mm |

Notes During processing, a dehumidifying hopper dryer is recommended at a temperature of 60 to 80°C.