



PRODUCT INFORMATION

TAROLOX 111 G8

PET medium viscosity 40% glass fibres reinforced, very good chemical resistance, good mechanical, thermal and electrical properties, low moisture absorption, good dimensional stability.

ISO short Form ISO 1043: PET-GF40
Pellets

Key Features

- Good impact - stiffness balance
- High stiffness
- Designed for injection moulding applications
- Glass fibres reinforced
- Excellent filling qualities
- Excellent surface smoothness
- Good surface aspect

Availability

- W: lubricated
- LP: laser printable
- L: UV stabilized
- H: heat stabilized
- All colours

Process

- INJECTION MOULDING

Application

- Electrical
- Automotive

Property	Method	Unit	Value	Condition	State
ELECTRICAL					
Electric Strength	IEC 60243-1	kV/mm	33	1 mm	
Tracking Resistance (CTI - Method A)	IEC 60112	Volt	250		
PHYSICAL					
Density (+23°C)	ISO 1183	g/cm ³	1,65		
Filler content	ISO 3451	%	40	750°C - 1 h	
Granule Humidity	Internal method	%	<0,03		
Water Absorption (24h / +23°C)	ISO 62	%	0,05		
Mould Shrinkage (Parallel)	Internal method	%	0,15 - 0,3		
Mould Shrinkage (Normal)	Internal method	%	0,4 - 0,6		



PRODUCT INFORMATION

TAROLOX 111 G8

Melting temperature (DSC)	ISO 11357	°C	256	
Melt Flow Rate (MFR)	ISO 1133	g/10 min	12	280°C - 2,16 kg

MECHANICAL

Tensile Modulus	ISO 527-1,2	MPa	14200	Speed 1 mm/min
Elongation at Break	ISO 527-1,2	%	1,8	Speed 50 mm/min
Tensile Break Strength	ISO 527-1,2	MPa	180	Speed 50 mm/min
Flexural Modulus	ISO 178	MPa	12500	Speed 1 mm/min
Flexural Break Strength	ISO 178	MPa	260	Speed 1 mm/min
IZOD Notched Impact (+23°C)	ISO 180/1A	kJ/m ²	9	
IZOD Notched Impact (+23°C)	ASTM D256	J/m	95	
CHARPY Notched Impact (+23°C)	ISO 179/1eA	kJ/m ²	11	
CHARPY Unnotched Impact (+23°C)	ISO 179/1eU	kJ/m ²	50	

THERMAL

Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	242	50°C / h
Deflection Temperature 1,80 MPa (HDT A)	ISO 75A	°C	230	120°C / h
Ball Pressure Test	IEC 60695-10-2	°C	245	
Coefficient of linear thermal expansion (parallel)	ISO 11359-1,-2	K ⁻¹	2,5x10E(-5)	-30°C /+30°C

FLAMMABILITY

Flame Behaviour (0,75 mm)	UL94	Class	HB	
Flame Behaviour (1,5 mm)	UL94	Class	HB	
Glow Wire Flammability Index-GWFI (2 mm)	IEC 60695-2-12	°C	750	
Burning Rate (US-FMVSS 302)	ISO 3795	mm/min	<80	Thickness > 1,5 mm

INJECTION MOULDING

	Value
Drying Temperature (Desiccant Dryer)	80 - 120 °C
Drying Time (Desiccant Dryer)	2 - 4 h
Suggested Max Moisture	< 0,03
Suggested Max Re grind	< 10%



PRODUCT INFORMATION

TAROLOX 111 G8

Melt Temperature	260 - 285°C
Feed Temperature	250°C
Rear Temperature	265°C
Middle Temperature	270°C
Front Temperature	275°C
Nozzle Temperature	275°C
Mould Temperature	60 - 100°C
Injection Rate	Medium to Fast
Injection Pressure	40 - 100 Mpa
Packing Pressure	30 - 80 Mpa
Back Pressure	0,5 - 1 Mpa
Screw Revolving Speed	70 rpm @ Diameter 60 mm
Screw Revolving Speed	95 rpm @ Diameter 45 mm
Screw Revolving Speed	140 rpm @ Diameter 30 mm
Screw Revolving Speed	220 rpm @ Diameter 20 mm
Cushion	2 - 6 mm
Screw L/D Ratio	18 - 22
Screw Compression Ratio	2:1 - 2,5:1
Vent Depth	0,02 mm

Notes During processing, a dehumidifying hopper dryer is recommended at a temperature of 60 to 80°C.