



PRODUCT INFORMATION

**TAROLOX 200 G2**

PBT/ASA alloy 10% glass fibres reinforced. Good flow, excellent surface aspect, good combination of mechanical and thermal properties, good dimensional stability and low warpage behaviour. Preliminary Data Sheet.

**ISO short Form** ISO 1043: PBT+ASA-GF10 Pellets

**Key Features**

- Designed for injection moulding applications
- Glass fibres reinforced
- Good flowability
- Good dimensional stability

**Availability**

- W: lubricated
- H: heat stabilized
- All colours

**Process**

- INJECTION MOULDING

**Application**

- Electronic
- Electrical
- Consumer
- Automotive

Property	Method	Unit	Value	Condition	State
<b>PHYSICAL</b>					
Density (+23°C)	ISO 1183	g/cm <sup>3</sup>	1,30		
Filler content	ISO 3451	%	10	750°C - 1 h	
Water Absorption (24h / +23°C)	ISO 62	%	0,05		
Water Absorption at Saturation	ISO 62	%	0,25		
Mould Shrinkage (Parallel)	Internal method	%	0,40 - 0,70		
Mould Shrinkage (Normal)	Internal method	%	0,60 - 0,90		
Melting temperature (DSC)	ISO 11357	°C	220		
Melt Flow Rate (MFR)	ISO 1133	g/10 min	8	250°C - 2,16 kg	
<b>MECHANICAL</b>					
Tensile Modulus	ISO 527-1,2	MPa	3900	Speed 1 mm/min	

PRODUCT INFORMATION

**TAROLOX 200 G2**

Elongation at Break	ISO 527-1,2	%	4,8	Speed 50 mm/min
Tensile Break Strength	ISO 527-1,2	MPa	65	Speed 50 mm/min
Flexural Modulus	ISO 178	MPa	3700	Speed 1 mm/min
Flexural Break Strength	ISO 178	MPa	110	Speed 1 mm/min
IZOD Notched Impact	ASTM D256	J/m	45	+23°C
CHARPY Notched Impact (+23°C)	ISO 179/1eA	kJ/m <sup>2</sup>	4,2	

**THERMAL**

Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	150	50°C / h
Deflection Temperature 1,80 MPa (HDT A)	ISO 75A	°C	145	120°C / h

**FLAMMABILITY**

Flame Behaviour (1,6 mm)	UL94	Class	HB	
Glow Wire Flammability Index-GWFI (2 mm)	IEC 60695-2-12	°C	650	
Burning Rate (US-FMVSS 302)	ISO 3795	mm/min	<100	
Oxygen index	ASTM D2863	%	20	

**INJECTION MOULDING**

	Value
Drying Temperature (Circulating Air Oven)	80 - 120°C
Drying Temperature (Desiccant Dryer)	80 - 120°C
Drying Time (Circulating Air Oven)	3 - 6 h
Drying Time (Desiccant Dryer)	2 - 4 h
Suggested Max Moisture	< 0,04%
Suggested Max Regrind	< 20%
Melt Temperature	250 - 270°C
Feed Temperature	60°C
Rear Temperature	235°C
Middle Temperature	245°C
Front Temperature	255°C
Nozzle Temperature	260°C
Mould Temperature	60 - 100°C
Injection Rate	Medium to Fast



PRODUCT INFORMATION

**TAROLOX 200 G2**

Injection Pressure	40 - 100 Mpa
Packing Pressure	30 - 80 Mpa
Back Pressure	0,5 - 1 Mpa
Screw Revolving Speed	70 rpm @ Diameter 60 mm
Screw Revolving Speed	95 rpm @ Diameter 45 mm
Screw Revolving Speed	140 rpm @ Diameter 30 mm
Screw Revolving Speed	220 rpm @ Diameter 20 mm
Screw Revolving Speed	300 rpm @ Diameter 15 mm
Cushion	2 - 6 mm
Screw L/D Ratio	18 - 22
Screw Compression Ratio	2:1 - 2,5:1
Vent Depth	0,02 mm

**Notes** During processing, a dehumidifying hopper dryer is recommended at a temperature of 60 to 80°C.