



PRODUCT INFORMATION

TAROMID A 280 G7

Polyamide 66 medium viscosity 35% glass fibre reinforced, good mechanical and thermal properties.

ISO short ISO 1043: PA66-GF35
Form Pellets
UL file E143048

Key Features

- Good impact - stiffness balance
- Designed for injection moulding applications
- Glass fibres reinforced

Availability

- W: lubricated
- LP: laser printable
- L: UV stabilized
- I: improved resistance to glycol-hydrolysis
- HT: high resistance to heat
- H: heat stabilized
- FA: food approval
- All colours

Compliance

- UL94 HB approved at 0,75 mm - NC (HW version only)

Process

- INJECTION MOULDING

Application

- Household
- Furniture
- Electronic
- Electrical
- Toys
- Sports
- Consumer
- Building
- Automotive

Property	Method	Unit	Value	Condition	State
ELECTRICAL					
Volume Resistivity	IEC 60093	Ohm cm	10E10		Cond.
Volume Resistivity	IEC 60093	Ohm cm	10E13		Dry
Dielectric Strength	IEC 60243-1	kV/mm	26	2 mm	

PRODUCT INFORMATION

TAROMID A 280 G7

Dielectric Constant (1 MHz)	IEC 60250	-	5,7	Cond.
Dielectric Constant (1 MHz)	IEC 60250	-	3,5	Dry
Dissipation Factor Frequency (1 MHz)	IEC 60250	-	3	Cond.
Dissipation Factor Frequency (1 MHz)	IEC 60250	-	0,2	Dry
Tracking Resistance (CTI - Method A)	IEC 60112	Volt	550	

PHYSICAL

Density (+23°C)	ISO 1183	g/cm ³	1,41	
Filler content	ISO 3451	%	35	750°C - 1 h
Granule Humidity	Internal method	%	< 0,10	
Water Absorption (24h / +23°C)	ISO 62	%	0,6	
Water Absorption at Saturation	ISO 62	%	4,6	
Mould Shrinkage (Parallel)	Internal method	%	0,25 - 0,35	
Mould Shrinkage (Normal)	Internal method	%	0,8 - 1,0	
Melting temperature (DSC)	ISO 11357	°C	256	
Melt Flow Rate (MFR)	ISO 1133	g/10 min	3,5	280°C - 1 kg
Melt Flow Rate (MFR)	ISO 1133	g/10 min	10	280°C - 2,16 kg

MECHANICAL

Tensile Modulus	ISO 527-1,2	MPa	8400	+23°C - Speed 1 mm/min	Cond.
Tensile Modulus	ISO 527-1,2	MPa	11200	+23°C - Speed 1 mm/min	Dry
Elongation at Break	ISO 527-1,2	%	5	+23°C - Speed 50 mm/min	Cond.
Elongation at Break	ISO 527-1,2	%	3	+23°C - Speed 50 mm/min	Dry
Tensile Break Strength	ISO 527-1,2	MPa	140	+23°C - Speed 50 mm/min	Cond.
Tensile Break Strength	ISO 527-1,2	MPa	200	+23°C - Speed 50 mm/min	Dry
Flexural Modulus	ISO 178	MPa	8300	+23°C - Speed 1 mm/min	Cond.
Flexural Modulus	ISO 178	MPa	10000	+23°C - Speed 1 mm/min	Dry
Flexural Break Strength	ISO 178	MPa	230	+23°C - Speed 1 mm/min	Cond.
Flexural Break Strength	ISO 178	MPa	290	+23°C - Speed 1 mm/min	Dry

PRODUCT INFORMATION

TAROMID A 280 G7

IZOD Notched Impact (+23°C)	ISO 180/1A	kJ/m ²	18	Cond.
IZOD Notched Impact (+23°C)	ISO 180/1A	kJ/m ²	14	Dry
IZOD Notched Impact (+23°C)	ASTM D256	J/m	165	Cond.
IZOD Notched Impact (+23°C)	ASTM D256	J/m	135	Dry
CHARPY Notched Impact (+23°C)	ISO 179/1eA	kJ/m ²	21,5	Cond.
CHARPY Notched Impact (+23°C)	ISO 179/1eA	kJ/m ²	13,5	Dry
CHARPY Unnotched Impact (+23°C)	ISO 179/1eU	kJ/m ²	105	Cond.
CHARPY Unnotched Impact (+23°C)	ISO 179/1eU	kJ/m ²	85	Dry
CHARPY Unnotched Impact (-30°C)	ISO 179/1eU	kJ/m ²	70	Dry

THERMAL

Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	254	50°C / h
Deflection Temperature 1,80 MPa (HDT A)	ISO 75A	°C	246	120°C / h
Deflection Temperature 0,45 MPa (HDT B)	ISO 75B	°C	250	120°C / h
Ball Pressure Test	IEC 60695-10-2	°C	230	
Continuous service temperature (20.000 h)	UL746 B	°C	100 (130H/HT)	
Continuous service temperature (short term)	UL746 B	°C	140 (180H/HT)	
Coefficient of linear thermal expansion (parallel)	ISO 11359-1,-2	K ⁻¹	2,0x10E(-5)	-30°C /+30°C
Coefficient of linear thermal expansion (transversal)	ISO 11359-1,-2	K ⁻¹	6,5x10E(-5)	-30°C /+30°C

FLAMMABILITY

Flame Behaviour (0,75 mm)	UL94	Class	HB	UL approved (HW version only)
Glow Wire Flammability Index-GWFI (2 mm)	IEC 60695-2-12	°C	750	
Oxygen index	ASTM D2863	%	27	

INJECTION MOULDING

	Value
Drying Temperature (Circulating Air Oven)	80 - 90°C
Drying Temperature (Desiccant Dryer)	80 - 90°C
Drying Time (Circulating Air Oven)	3 - 6 hours
Drying Time (Desiccant Dryer)	2 - 4 hours
Suggested Max Moisture	<0,08 %

PRODUCT INFORMATION

TAROMID A 280 G7

Suggested Max Regrind	<15 %
Melt Temperature	270 - 300°C
Feed Temperature	100°C
Rear Temperature	275°C
Middle Temperature	285°C
Front Temperature	285°C
Nozzle Temperature	280°C
Mould Temperature	80 - 120°C
Injection Rate	Medium to fast (50 - 150 mm/sec)
Injection Pressure	80 - 130 Mpa
Packing Pressure	30 - 80 Mpa
Back Pressure	0,3 - 0,7 Mpa
Screw Revolving Speed	50 - 100 rpm
Cushion	2 - 6 mm
Screw L/D Ratio	18 - 22
Screw Compression Ratio	2:1 - 3:1
Vent Depth	0,02 mm

Notes During processing, a dehumidifying hopper dryer is recommended at a temperature of 60 to 80°C.