

PRODUCT INFORMATION

TAROMID B 280 G6 X0

Polyamide 6 medium viscosity 30% glass fibres reinforced, flame retardant UL94 V0, good flame proofing also at low thickness, good flow and mechanical properties, good dimensional stability.

ISO short ISO 1043: PA6-GF30 FR(17)
Form Pellets
UL file E143048

Key Features

- Designed for injection moulding applications
- Glass fibres reinforced
- Flame retardant
- Good flowability

Availability

- LP: laser printable
- L: UV stabilized
- H: heat stabilized
- All colours

Process

- INJECTION MOULDING

Application

- Electronic
- Electrical

Property	Method	Unit	Value	Condition	State
ELECTRICAL					
Volume Resistivity	IEC 60093	Ohm cm	10E(15)		
Dielectric Strength	IEC 60243-1	kV/mm	21		
Tracking Resistance (CTI - Method A)	IEC 60112	Volt	400		
PHYSICAL					
Density (+23°C)	ISO 1183	g/cm ³	1,57		
Filler content	ISO 3451	%	30	850°C - 1 h	
Water Absorption (24h / +23°C)	ISO 62	%	0,8		
Water Absorption at Saturation	ISO 62	%	6		
Mould Shrinkage (Parallel)	Internal method	%	0,25 - 0,40		
Mould Shrinkage (Normal)	Internal method	%	0,40 - 0,60		
Melting temperature (DSC)	ISO 11357	°C	222		

MECHANICAL

PRODUCT INFORMATION

TAROMID B 280 G6 X0

Tensile Modulus	ISO 527-1,2	MPa	5700		Cond.
Tensile Modulus	ISO 527-1,2	MPa	9500	Speed 1 mm/min	Dry
Elongation at Break	ISO 527-1,2	%	2,9		Cond.
Elongation at Break	ISO 527-1,2	%	2,2	Speed 50 mm/min	Dry
Tensile Break Strength	ISO 527-1,2	MPa	85		Cond.
Tensile Break Strength	ISO 527-1,2	MPa	130	Speed 50 mm/min	Dry
Flexural Modulus	ISO 178	MPa	9000	Speed 1 mm/min	Dry
Flexural Break Strength	ISO 178	MPa	200	Speed 1 mm/min	Dry
IZOD Notched Impact (+23°C)	ASTM D256	J/m	85		Dry
CHARPY Notched Impact (+23°C)	ISO 179/1eA	kJ/m ²	8,2		Dry
CHARPY Unnotched Impact (+23°C)	ISO 179/1eU	kJ/m ²	48		Cond.
CHARPY Unnotched Impact (+23°C)	ISO 179/1eU	kJ/m ²	40		Dry

THERMAL

Softening Temperature - 1 kg (VST/A/50)	ISO 306	°C	216		
Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	212		
Deflection Temperature 1,80 MPa (HDT A)	ISO 75A	°C	208		
Ball Pressure Test	IEC 60695-10-2	°C	170		
Continuous service temperature (20.000 h)	UL746 B	°C	120		
Continuous service temperature (short term)	UL746 B	°C	160		
Coefficient of linear thermal expansion (parallel)	ISO 11359-1,-2	K ⁻¹	3,2x10E(-5)	- 30°C / + 30°C	

FLAMMABILITY

Flame Behaviour (0,97 mm)	UL94	Class	V0	UL approved	
Flame Behaviour (1,5 mm)	UL94	Class	V0		
Glow Wire Flammability Index-GWFI (1 mm)	IEC 60695-2-12	°C	960		
Glow Wire Ignition Temperature-GWIT (1,6 mm)	IEC 60695-2-13	°C	825		
Oxygen index	ASTM D2863	%	32		

INJECTION MOULDING

Value

PRODUCT INFORMATION

TAROMID B 280 G6 X0

Drying Temperature (Desiccant Dryer)	80 - 90°C
Drying Time (Desiccant Dryer)	2 - 4 hours
Suggested Max Moisture	0,08 %
Suggested Max Regrind	< 10 %
Melt Temperature	230 - 260°C
Feed Temperature	210°C
Rear Temperature	235°C
Middle Temperature	245°C
Front Temperature	255°C
Nozzle Temperature	250°C
Mould Temperature	70 - 100°C
Injection Rate	Medium to Fast
Injection Pressure	3 - 12 Mpa
Packing Pressure	5 - 15 Mpa
Screw Revolving Speed	50 - 100 rpm
Cushion	> 3 mm
Screw L/D Ratio	18 - 22
Screw Compression Ratio	2:1 - 2,5:1
Vent Depth	0,02 mm

Notes During processing, a dehumidifying hopper dryer is recommended at a temperature of 60 to 80°C.