



PRODUCT INFORMATION

## TAROMID B 280 R2

Polyamide 6 medium viscosity elastomer modified, high impact resistance, no conditioning required.

**ISO short Form** ISO 1043: PA6-I Pellets

### Key Features

- Unfilled
- Improved impact resistance
- Designed for injection moulding applications
- Good flowability

### Availability

- W: lubricated
- L: UV stabilized
- H: heat stabilized
- All colours

### Process

- INJECTION MOULDING

### Application

- Household
- Furniture
- Electrical
- Consumer
- Automotive

Property	Method	Unit	Value	Condition	State
<b>ELECTRICAL</b>					
Volume Resistivity	IEC 60093	Ohm cm	5x10exp(15)		
Dielectric Strength	IEC 60243-1	kV/mm	18	2 mm	
Tracking Resistance (CTI - Method A)	IEC 60112	Volt	600		
<b>PHYSICAL</b>					
Density (+23°C)	ISO 1183	g/cm <sup>3</sup>	1,11		
Granule Humidity	Internal method	%	< 0,15		
Water Absorption (24h / +23°C)	ISO 62	%	1,3		
Water Absorption at Saturation	ISO 62	%	8		
Mould Shrinkage (Parallel)	Internal method	%	1,1 - 1,5		
Mould Shrinkage (Normal)	Internal method	%	1,1 - 1,5		

PRODUCT INFORMATION

**TAROMID B 280 R2**

Melting temperature (DSC)	ISO 11357	°C	220
---------------------------	-----------	----	-----

**MECHANICAL**

Hardness SHORE D	ASTM D2240	Shore D	68	3 sec
Tensile Modulus	ISO 527-1,2	MPa	2400	Speed 1 mm/min Dry
Tensile Yield Strength	ISO 527-1,2	MPa	65	Speed 50 mm/min Dry
Elongation at Break	ISO 527-1,2	%	20	Speed 50 mm/min Dry
Flexural Modulus	ISO 178	MPa	2000	Speed 1 mm/min Dry
IZOD Notched Impact (+23°C)	ASTM D256	J/m	200	Dry
IZOD Unnotched Impact (+23°C)	ASTM D256	J/m	NB	Dry
CHARPY Notched Impact (+23°C)	ISO 179/1eA	kJ/m <sup>2</sup>	25	Dry

**THERMAL**

Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	175	50°C / h
Deflection Temperature 1,80 MPa (HDT A)	ISO 75A	°C	70	120°C / h

**FLAMMABILITY**

Flame Behaviour (1,6 mm)	UL94	Class	HB
--------------------------	------	-------	----

**INJECTION MOULDING**

	Value
Drying Temperature (Circulating Air Oven)	80 - 90°C
Drying Temperature (Desiccant Dryer)	80 - 90°C
Drying Time (Circulating Air Oven)	3 - 6 h
Drying Time (Desiccant Dryer)	2 - 4 h
Suggested Max Moisture	< 0,08%
Suggested Max Regrind	< 15%
Melt Temperature	240 - 260°C
Feed Temperature	220°C
Rear Temperature	235°C
Middle Temperature	245°C
Front Temperature	250°C
Nozzle Temperature	245°C
Mould Temperature	70 - 80°C

PRODUCT INFORMATION

**TAROMID B 280 R2**

Injection Rate	Medium to Fast
Injection Pressure	40 - 100 Mpa
Packing Pressure	30 - 80 Mpa
Back Pressure	0,5 - 2,5 Mpa
Screw Revolving Speed	50 - 100 rpm
Cushion	2 - 6 mm
Screw L/D Ratio	18 - 22
Screw Compression Ratio	2:1 - 2,5:1
Vent Depth	0,02 mm

**Notes** During processing, a dehumidifying hopper dryer is recommended at a temperature of 60 to 80°C. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine or extruder size, part geometry and design.