



PRODUCT INFORMATION

TAROMID B 280 Z2

Polyamide 6 medium viscosity impact modified, very high impact resistance also at low temperature.

ISO short Form ISO 1043: PA6-I Pellets

Key Features

- Unfilled
- High mechanical properties
- Good impact - stiffness balance
- Improved impact resistance
- Suitable for injection moulding and extrusion applications
- Low flow

Availability

- White colour
- S: fast injection cycles
- LP: laser printable
- L: UV stabilized
- HT: high resistance to heat
- H: heat stabilized
- DB: dry blend coloured
- All colours

Process

- INJECTION MOULDING
- EXTRUSION

Application

- Gears
- Power tools
- Household
- General purpose applications
- Furniture
- Electronic
- Electrical
- Sports
- Consumer
- Building
- Automotive

Property	Method	Unit	Value	Condition	State
----------	--------	------	-------	-----------	-------

ELECTRICAL

Volume Resistivity	IEC 60093	Ohm cm	10E(13)		Cond.
--------------------	-----------	--------	---------	--	-------

PRODUCT INFORMATION

TAROMID B 280 Z2

Volume Resistivity	IEC 60093	Ohm cm	10E(15)	Dry
Tracking Resistance (CTI - Method A)	IEC 60112	Volt	> 600	

PHYSICAL

Density (+23°C)	ISO 1183	g/cm ³	1,11	
Granule Humidity	Internal method	%	< 0,15	
Water Absorption (24h / +23°C)	ISO 62	%	0,8	
Water Absorption at Saturation	ISO 62	%	5,5	
Mould Shrinkage (Parallel)	Internal method	%	1,0 - 1,5	
Mould Shrinkage (Normal)	Internal method	%	1,0 - 1,5	
Melting temperature (DSC)	ISO 11357	°C	225	

MECHANICAL

Tensile Modulus	ISO 527-1,2	MPa	1500	Speed 1 mm/min	Cond.
Tensile Modulus	ISO 527-1,2	MPa	2000	Speed 1 mm/min	Dry
Tensile - Yield Strain	ISO 527-1,2	%	10	Speed 50 mm/min	Cond.
Tensile - Yield Strain	ISO 527-1,2	%	5	Speed 50 mm/min	Dry
Tensile Yield Strength	ISO 527-1,2	MPa	35	Speed 50 mm/min	Cond.
Tensile Yield Strength	ISO 527-1,2	MPa	50	Speed 50 mm/min	Dry
Elongation at Break	ISO 527-1,2	%	> 100	Speed 50 mm/min	Cond.
Elongation at Break	ISO 527-1,2	%	> 80	Speed 50 mm/min	Dry
Tensile Break Strength	ISO 527-1,2	MPa	32	Speed 50 mm/min	Cond.
Tensile Break Strength	ISO 527-1,2	MPa	45	Speed 50 mm/min	Dry
Flexural Modulus	ISO 178	MPa	1300	Speed 1 mm/min	Cond.
Flexural Modulus	ISO 178	MPa	1800	Speed 1 mm/min	Dry
Flexural Max Strength	ISO 178	MPa	35	Speed 10 mm/min	Cond.
Flexural Max Strength	ISO 178	MPa	48	Speed 10 mm/min	Dry
IZOD Notched Impact (+23°C)	ASTM D256	J/m	380		Cond.
IZOD Notched Impact (+23°C)	ASTM D256	J/m	250		Dry

PRODUCT INFORMATION

TAROMID B 280 Z2

CHARPY Notched Impact (+23°C)	ISO 179/1eA	kJ/m ²	45	Cond.
CHARPY Notched Impact (+23°C)	ISO 179/1eA	kJ/m ²	20	Dry
CHARPY Unnotched Impact (+23°C)	ISO 179/1eU	kJ/m ²	N.B.	Cond.
CHARPY Unnotched Impact (+23°C)	ISO 179/1eU	kJ/m ²	N.B.	Dry

THERMAL

Softening Temperature - 5 kg (VST/B/50)	ISO 306	°C	130	50°C / h
Deflection Temperature 1,80 MPa (HDT A)	ISO 75A	°C	70	120°C / h
Continuous service temperature (20.000 h)	UL746 B	°C	80	
Continuous service temperature (short term)	UL746 B	°C	100	

FLAMMABILITY

Flame Behaviour (1,6 mm)	UL94	Class	HB	
Glow Wire Flammability Index-GWFI (2 mm)	IEC 60695-2-12	°C	650	
Oxygen Index Test (L.O.I.)	ISO 4589-2	%	22	

EXTRUSION

	Value
Drying Time (Desiccant Dryer)	2 - 4 hours
Drying Temperature (Desiccant Dryer)	80 - 90°C
Suggested Max Moisture	0,08%
Suggested Max Regrind	< 10%
Melt Temperature	240 - 260°C
Feed Temperature	225°C
Rear Temperature	230°C
Middle Temperature	240°C
Front Temperature	250°C
Die Temperature	245°C
Screw Revolving Speed	50 - 100 rpm
Screw L/D Ratio	25 to 30
Screw Compression Ratio	3:1 to 4:1

Notes During processing, a dehumidifying hopper dryer is recommended at a temperature of 60 to 80°C. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine or extruder size, part geometry and design.

PRODUCT INFORMATION

TAROMID B 280 Z2

INJECTION MOULDING	Value
Drying Temperature (Circulating Air Oven)	80 - 90°C
Drying Temperature (Desiccant Dryer)	80 - 90°C
Drying Time (Circulating Air Oven)	3 - 6 h
Drying Time (Desiccant Dryer)	2 - 4 h
Suggested Max Moisture	< 0,08 %
Suggested Max Regrind	< 15 %
Melt Temperature	240 - 260°C
Feed Temperature	220°C
Rear Temperature	235°C
Middle Temperature	245°C
Front Temperature	250°C
Nozzle Temperature	245°C
Mould Temperature	70 - 80°C
Injection Rate	Medium to Fast
Injection Pressure	40 - 100 Mpa
Packing Pressure	30 - 80 Mpa
Back Pressure	0,5 - 2,5 Mpa
Screw Revolving Speed	50 - 100 rpm
Cushion	2 - 6 mm
Screw L/D Ratio	18 - 22
Screw Compression Ratio	2:1 - 2,5:1
Vent Depth	0,02 mm

Notes During processing, a dehumidifying hopper dryer is recommended at a temperature of 60 to 80°C. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine or extruder size, part geometry and design.