



PRODUCT INFORMATION

TAROPRENE 2A60 E1G

Thermoplastic Elastomer Vulcanized. This TPE-V compound combines the typical performance of a vulcanized elastomer with the easy processing of a thermoplastic compound. Taroprene is totally recyclable and it can be produced in standard grades and in tailor-made grades.

ISO short Form ISO 18064: TPV-(EPDM+PP)
Pellets

Key Features

- Very light natural colour
- Designed for extrusion applications

Process

- INJECTION MOULDING

Application

- Household
- General purpose applications
- Furniture
- Consumer
- Building
- Automotive

Property	Method	Unit	Value	Condition	State
PHYSICAL					
Density (+23°C)	ISO 1183	g/cm ³	0,96		
Melt Flow Rate (MFR)	ISO 1133	g/10 min	6,0	190°C - 5 kg	
MECHANICAL					
Hardness SHORE A	ASTM D2240	Shore A	60	3 sec	
Tensile Break Strength	ASTM D412/C	MPa	5,2		
Elongation at Break	ASTM D412/C	%	610		
Tensile Modulus at 100% elongation	ASTM D412/C	MPa	1,96		
Tensile Modulus at 300% Elongation	ASTM D412/C	MPa	3,44		
Tear Strength	ASTM D624/C	N/mm	28		



PRODUCT INFORMATION

TAROPRENE 2A60 E1G

Compression Set	ASTM D395/B	%	35	70°C - 22h
Compression Set	ASTM D395/B	%	42	100°C - 22h

INJECTION MOULDING	Value
Drying Temperature (Desiccant Dryer)	80 - 90°C
Drying Time (Desiccant Dryer)	3 h
Melt Temperature	190 - 220°C
Rear Temperature	180°C
Middle Temperature	190°C
Front Temperature	200°C
Die Temperature	210°C

Notes TAROPRENE is incompatible with POM and PVC. We recommend that all TAROPRENE products are always dried prior to use at the specified drying conditions.