

General Homo PP for Yarn

YUHWA POLYPRO 5014U

Features
and Uses

Properties

Application	General Homo PP for Yarn			
Features	Weatherability			
Uses	Fishing Nets, Ropes, Band Packaging Tapes			
	Items	Specification	Unit	Test Method
	Melt Index	3.5	g/10min.	ASTM D1238
	Density	0.9	g/cm ³	ASTM D1505
	Mold Shrinkage	1.0~2.0	%	KPIC Method
	Water Absorption	<0.01	%	ASTM D570
	Tensile Strength at Yield	360	kgf/cm ²	ASTM D638
	Elongation at Break	>500	%	ASTM D638
	Flexural Modulus	15,000	kgf/cm ²	ASTM D790
	Hardness (Rockwell)	96	R Scale	ASTM D785
	Impact Strength (Izod with Notch)	4	kgf cm/cm	ASTM D256
	Melting Point	162	°C	ASTM D3418
	Softening Point (Vicat)	152	°C	ASTM D1525
	Heat Deflection Temperature	105	°C	ASTM D648

※ Above data are intended to serve as guides only, and are not sales specification limits.

Contact
Info.

Division	Team in charge	TEL	FAX	e-mail
International Trade	KPICC	82-2-3706-0844, 0849	82-2-3706-0893, 0894	trade@kpicc.com
Technical Service	Marketing Support Team	82-2-2122-1537	82-2-2122-1519	H15106@kpic.co.kr