



Rynite® PET

thermoplastic polyester resin

Rynite® 830ER NC010

Rynite® 830ER is 30% glass reinforced with excellent high temperature dielectric properties. Class H (180C).

Property	Test Method	Units	Value
Mechanical			
Tensile Strength	ASTM D 638	MPa (kpsi)	
-40C (-40F)			193 (28)
23C (73F)			169 (24.6)
93C (200F)			107 (15.6)
150C (300F)			68 (9.9)
Elongation at Break	ASTM D 638	%	
-40C (-40F)			2.1
23C (73F)			2.3
93C (200F)			3.6
150C (300F)			6.5
Tensile Modulus	ASTM D 638	MPa (kpsi)	
-40C (-40F)			11200 (1630)
23C (73F)			10700 (1560)
93C (200F)			7590 (1100)
150C (300F)			4380 (635)
Shear Strength	ASTM D 732	MPa (kpsi)	74.5 (10.8)
Flexural Modulus	ASTM D 790	MPa (kpsi)	
-40C (-40F)			9660 (1400)
23C (73F)			8960 (1300)
93C (200F)			3990 (579)
150C (300F)			2800 (406)
Flexural Strength	ASTM D 790	MPa (kpsi)	
-40C (-40F)			276 (40)
23C (73F)			240 (35)
93C (200F)			98.6 (14.3)
150C (300F)			82.3 (12)

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.

Mechanical properties measured at 23°C (73°F) unless otherwise stated.

Shrinkage generated per ISO 294-4 based on 60 X 60mm end-gated plaques or ASTM D 955 based on 76 X 127mm (3 X 5in) end-gated plaques.

Rynite® is a DuPont registered trademark.

991001/991208

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-51459 or H-50102.

Start with DuPont Engineering Polymers - www.dupont.com/enggpolymer

Product Information

Rynite® 830ER NC010

Property	Test Method	Units	Value
Mechanical			
Compressive Strength	ASTM D 695	MPa (kpsi)	241 (35)
Deformation Under Load 27.6MPa (4000psi)	ASTM D 621	%	0.3
Izod Impact	ASTM D 256	J/m (ft lb/in)	
-40C (-40F)			85 (1.6)
23C (73F)			90 (1.7)
Unnotched Impact	ASTM D 4812	J/m (ft lb/in)	
-40C (-40F)			640 (12)
23C (73F)			695 (13)
Thermal			
Heat Deflection Temperature	ASTM D 648	°C (°F)	
0.45MPa (66psi)			251 (484)
1.8MPa (264psi)			233 (451)
CLTE, Parallel	ASTM E 228	E-4/C (E-4/F)	
-40 - 23C (-40 - 73F)			0.21 (0.12)
23 - 55C (73 - 130F)			0.19 (0.11)
55 - 160C (130 - 320F)			0.12 (0.07)
CLTE, Normal	ASTM E 228	E-4/C (E-4/F)	
-40 - 23C (-40 - 73F)			0.56 (0.31)
23 - 55C (73 - 130F)			0.60 (0.33)
55 - 160C (130 - 320F)			0.90 (0.50)
Thermal Conductivity	ASTM C 177	W/m K (Btu in/h ft ² F)	
23C (73F)			0.32 (2.2)
50C (122F)			0.3 (2)
100C (212F)			0.31 (2.1)

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.

Mechanical properties measured at 23°C (73°F) unless otherwise stated.

Shrinkage generated per ISO 294-4 based on 60 X 60mm end-gated plaques or ASTM D 955 based on 76 X 127mm (3 X 5in) end-gated plaques.

Rynite® is a DuPont registered trademark.

991001/991208

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-51459 or H-50102.

Start with DuPont Engineering Polymers - www.dupont.com/engpolymers

Rynite® 830ER NC010

Property	Test Method	Units	Value
Electrical			
Surface Resistivity	ASTM D 257	ohm	1 E13
Volume Resistivity	ASTM D 257	ohm cm	1 E15
Dielectric Strength, Short Time	ASTM D 149	kV/mm (V/mil)	
23C (73F), 1.57mm (0.062in)			25 (635)
23C (73F), 3.2mm (0.126in)			121.5 (550)
95C (200F), 1.57mm (0.062in)			23 (585)
95C (200F), 3.2mm (0.126in)			19 (485)
150C (300F), 1.57mm (0.062in)			23.5 (600)
150C (300F), 3.2mm (0.126in)			19 (485)
200C (390F), 1.57mm (0.062in)			21.5 (550)
200C (390F), 3.2mm (0.126in)			15 (380)
Dielectric Constant	ASTM D 150		
1E3 Hz			4.2
1E6 Hz			4.1
Dissipation Factor	ASTM D 150		
1E3 Hz			0.004
1E6 Hz			0.014
Flammability			
Rating @ Thickness	UL94		HB
Thickness Tested	UL94	mm	0.75
Other			
Specific Gravity	ASTM D 792		1.58
Hardness, Rockwell	ASTM D 785		
Scale M			100
Scale R			120
Water Absorption	ASTM D 570	%	
50%RH,23C,24h			0.06
Mold Shrinkage	ASTM D 955	%	
Flow, 1.57mm (0.062in)			0.13
Flow, 3.2mm (0.126in)			0.15
Transverse, 1.57mm (0.062in)			0.6
Transverse, 3.2mm (0.126in)			0.7
Processing			
Melt Temperature Range		°C (°F)	280-300 (535-570)
Mold Temperature Range		°C (°F)	>95 (>205)
Drying Time, Dehumidified Dryer		h	4
Drying Temperature		°C (°F)	120 (250)
Processing Moisture Content		%	<0.02

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.

Mechanical properties measured at 23°C (73°F) unless otherwise stated.

Shrinkage generated per ISO 294-4 based on 60 X 60mm end-gated plaques or ASTM D 955 based on 76 X 127mm (3 X 5in) end-gated plaques.

Rynite® is a DuPont registered trademark.

991001/991208

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-51459 or H-50102.

Start with DuPont Engineering Polymers - www.dupont.com/enggpolymer