

Panlite® LN-1010RM

TEIJIN LIMITED - Polycarbonate

General Information

Product Description

High light reflection grade, Halogen type flame resistant grade

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Flame Retardant		• High Reflectivity
Uses	• LEDs	• Lighting Applications	• Reflectors
Appearance	• White		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.33	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow : 4.00 mm	0.40 to 0.60	%	
Flow : 4.00 mm	0.40 to 0.60	%	
Water Absorption (24 hr, 23°C)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2500	MPa	ISO 527-2/1
Tensile Stress (Yield)	54.0	MPa	ISO 527-2/50
Tensile Stress (Break)	50.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	6.0	%	ISO 527-2/50
Tensile Strain (Break)	110	%	ISO 527-2/50
Flexural Modulus ²	2300	MPa	ISO 178
Flexural Stress ²	91.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	25	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	No Break		ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	137	°C	ISO 75-2/B
Heat Deflection Temperature (1.8 MPa, Unannealed)	125	°C	ISO 75-2/A
Vicat Softening Temperature	139	°C	ISO 306/B50
CLTE - Flow	7.0E-5	cm/cm/°C	ISO 11359-2
CLTE - Transverse	7.0E-5	cm/cm/°C	ISO 11359-2
RTI Elec (1.5 mm)	80.0	°C	UL 746
RTI Imp (1.5 mm)	80.0	°C	UL 746
RTI Str (1.5 mm)	80.0	°C	UL 746

Panlite® LN-1010RM

TEIJIN LIMITED - Polycarbonate

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Electric Strength ³	32	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	3.40		
1 MHz	3.40		
Dissipation Factor			IEC 60250
100 Hz	2.7E-3		
1 MHz	0.010		
Comparative Tracking Index	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating ⁴ (0.38 mm)	V-0		UL 94

Notes

¹ Typical properties: these are not to be construed as specifications.

² 2.0 mm/min

³ short time test

⁴ white