



Polyethylene Bormed™ HE2581-PH

Description

Bormed HE2581-PH is a resin intended for evaluation for use in Healthcare applications.

Bormed HE2581-PH is a bimodal high density polyethylene typically used for blow moulding of articles up to 10 litres. Material is characterised by easy processing and products with high stiffness and very good environmental stress crack resistance (ESCR). Material can also be used for containers produced with IBM technology. Material can be sterilised with ethylene oxide, steam and radiation up till 35 kGy; as a result of sterilisation by radiation some minor yellowing can occur.

Applications

Bormed HE2581-PH has been evaluated according to different regulations and norms. Typical applications are mentioned below for Medical devices or Pharmaceutical & Diagnostic packaging. However, Borealis should be consulted for final approval to evaluate the use of Bormed HE2581-PH.

Bottles and containers for tablets
Bottles and containers for powder
Bottles and containers for granules

Bottles for IV-solutions
Bottles for irrigation solutions
Containers for fine chemicals or APIs

This grade may only be used for the applications listed in the Product Datasheet and only to the extent that the application is within the scope of the tests set out in the Statement on Compliance to Regulations on Medical Use for that grade. If an application is not listed in the Product Datasheet, the grade can be used for such application only after express written consent of the Borealis Marketing Manager, Healthcare.

Borealis prohibits the use of any healthcare grade product in an implantable device that is introduced into the human body by surgical intervention and that is intended to remain in place following surgical procedure.

Special features

Easy processing
Low extractables

High ESCR

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	958 kg/m ³	ISO 1183
Melt Flow Rate (190 °C/2,16 kg)	0,3 g/10min	ISO 1133
Melt Flow Rate (190 °C/5 kg)	1,3 g/10min	ISO 1133
Melt Flow Rate (190 °C/21,6 kg)	28 g/10min	ISO 1133
Flexural Modulus (2 mm/min)	1.400 MPa	ISO 178
Tensile Modulus (1 mm/min)	1.300 MPa	ISO 527-2
Tensile Strain at Yield (50 mm/min)	8 %	ISO 527-2
Tensile Stress at Yield (50 mm/min)	29 MPa	ISO 527-2
Heat Deflection Temperature (0,45 MPa)	80 °C	ISO 75-2
Environmental Stress Crack Resistance (Antarox 10 %),	100 h	ASTM D 1693-A

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



Polyethylene

Bormed HE2581-PH

(F50)
Hardness, Shore D

63

ISO 868

Processing Techniques

Following parameters should be used as guidelines:

Bormed HE2581-PH is easy to extrude and can be used in all conventional blow-moulding machines

Barrel	170 - 190 °C
Die	175 - 190 °C
Melt temperature	170 - 200 °C

Storage

Bormed HE2581-PH should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

Safety

The product is not classified as dangerous.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"
 Recovery and disposal of polyolefins
 Information on emissions from processing and fires
 Statement on compliance to food contact regulations
 Statement on polymer additives and BSE
 Statement on chemicals, regulations and standards
 Statement on compliance to regulations on medical use

HongRong Engineering Plastics Co.,Ltd.
 Head Office Tel. +85-2-6957-5415
 Research Center Tel.+188 1699 6168



Polyethylene

Bormed HE2581-PH

Disclaimer

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.