



Polyethylene Bormed™ LE6607-PH

Description

Bormed LE6607-PH is a resin intended for evaluation for use in Healthcare applications.

Bormed LE6607-PH is an additive free low density polyethylene typically used in blow moulding articles. Material is characterised with a balanced in flexibility to facilitate to collapsibility of containers. Bottles and ampoules made from Bormed LE6607PH can be steam sterilised at maximum 110 °C. Products made from Bormed LE6607-PH can be sterilised by using ethylene oxide or radiation up to 35 kGy.

Applications

Bormed LE6607-PH has been evaluated according to different regulations and norms. Typical applications are mentioned below for Medical devices or Pharmaceutical & Diagnostic packaging. However, Borealis should be consulted for final approval to evaluate the use of Bormed LE6607-PH .

Bottles for irrigation solutions
Bottles for IV-solutions

Ampoules for injectable solutions

This grade may only be used for the applications listed in the Product Datasheet and only to the extent that the application is within the scope of the tests set out in the Statement on Compliance to Regulations on Medical Use for that grade. If an application is not listed in the Product Datasheet, the grade can be used for such application only after express written consent of the Borealis Marketing Manager, Healthcare. Borealis prohibits the use of any healthcare grade product in an implantable device that is introduced into the human body by surgical intervention and that is intended to remain in place following surgical procedure.

Special features

No additives

Physical Properties

Property	Typical Value	Test Method
	Data should not be used for specification work	
Density	927 kg/m ³	ISO 1183
Melt Flow Rate (190 °C/2,16 kg)	0,3 g/10min	ISO 1133
Flexural Modulus	290 MPa	ISO 178
Tensile Modulus (1 mm/min)	300 MPa	ISO 527-2
Tensile Strain at Break (50 mm/min)	350 %	ISO 527-2
Tensile Stress at Yield (50 mm/min)	12 MPa	ISO 527-2
Heat Deflection Temperature (0,45 MPa)	51 °C	ISO 75-2
Hardness, Shore D	52	ISO 868

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



Polyethylene

Bormed LE6607-PH

Processing Techniques

Following parameters should be used as guidelines:

Bormed LE6607-PH is easy to extrude and can be used in all conventional blow-moulding machines

Melt temperature 165 - 200 °C

Storage

Bormed LE6607-PH should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety of the product.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"

Recovery and disposal of polyolefins

Information on emissions from processing and fires

Statement on chemicals, regulations and standards

Statement on compliance to food contact regulations

Statement on compliance to regulations on medical use



Polyethylene

Bormed LE6607-PH

Disclaimer

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.