



Polyethylene FA3227

Low density polyethylene for Film Extrusion

Description

FA3227 is a low density polyethylene produced in a high-pressure process.

FA3227 is a Low Density Polyethylene for Film Extrusion, UV stabilised.

This grade is suitable for building and construction film and meets the requirements for heat, alkali and UV resistance described in the building standards from the Nordic countries. A 150-micron film based upon FA3227 will last at least four times as long as an unstabilised film of the same thickness.

CAS-No. 9002-88-4

Applications

FA3227 has been developed especially for applications like:

Construction films
Heavy-duty sack

Shrink film
Liners

Additives

FA3227 is UV stabilised.

Physical Properties

Property	Typical Value	Test Method
Density	922 kg/m ³	ISO 1183
Melt Flow Rate (190 °C/2,16 kg)	0,3 g/10min	ISO 1133
Melting temperature	110 °C	ISO 11357-3

Data should not be used for specification work

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



Polyethylene FA3227

Film Properties

Film properties are measured on 125 µm sample produced on a 60 mm W&H extruder with IBC cooling at BUR = 1:2,5.

Property	Typical Value	Test Method
	Data should not be used for specification work	
Dart Drop	450 g	ISO 7765-1
Puncture resistance	5 J	ASTM D 5748
Tensile Strain at Break ¹	MD 400 %	ISO 527-3
Tensile Strain at Break	TD 600 %	ISO 527-3
Tensile Strength (22 mm/min) (24 °C)	MD 25 MPa	ISO 527-3
Tensile Strength (22 mm/min) (24 °C)	TD 23 MPa	ISO 527-3
Tensile Modulus	MD 190 MPa	ASTM D 882-A
Tensile Modulus	TD 190 MPa	ASTM D 882-A
Tear resistance (Elmendorf)	MD 5 N	ISO 6383/2
	TD 6 N	
Coefficient of friction (Dynamic)	0,6	ISO 8295

¹ MD = machine direction, TD = transverse direction.

Processing Techniques

FA3227 is easily processed on conventional extruders.

With suitable equipment FA3227 can be drawn down to 70-75 micron.

Recommended melt temperature range is from 170°C to 200°C.

Due to differences in screw and die head designs the optimum temperature adjustments are individual and should be sought for each production line.

Storage

FA3227 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet".

Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



Polyethylene FA3227

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"
Statement on chemicals, regulations and standards
Statement on compliance to food contact regulations

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.