

Stamylex[®] 5119 S

Medium density linear polyethylene

DATA SHEET

Description

Stamylex[®] 5119 S is a medium density linear polyethylene produced in a solution polymerisation process using a Ziegler – Natta catalyst. This grade contains an additive package for thermal stabilization and a processing aid.

Stamylex 5119 S offers a combination of :

- good flow properties
- mechanical properties
- narrow additive tolerances

Applications

Stamylex 5119 S is suited for use in caps of non-carbonated mineral water bottles, afforded by good closing properties, unscrewing torque and organoleptic properties. The material is designed for trouble-free operation on fast bottle filling lines.


<i>General properties</i>	<i>Units</i>	<i>Typical values</i>	<i>Method</i>
Melt Flow Rate (2.16 kg/190°C)	dg/min	11	ISO 1133
Density (23°C)	kg/m ³	944	ISO 1183

<i>Moulded plaque properties</i>	<i>Units</i>	<i>Typical values</i>	<i>Method</i>
Tensile test [1]			ISO 527-2
Stress at break [2]	MPa	12	
Strain at break [2]	%	40	
Modulus of elasticity in tension	MPa	700	
Notched Izod at + 23 °C	kJ/m ³	3.7	ISO 180 (1A)
Hardness Shore D		57	ISO 868

<i>Thermal properties</i>			
Vicat softening temperature at 10 N	°C	115	ISO 306
DSC melting point	°C	125	ASTM D3418

[1] Test specimen as per ISO 527-2 type 1 BA, thickness 2 mm
 [2] Speed of testing : 500 mm/min

Stamylex 5119 S



Food Law Compliance and Product Handling

Detailed and specific information on food law compliance and material safety aspects of Stamylex grades will be provided upon request.

Standard Packaging

Stamylex 5119 S is supplied as free flowing pellets in bulk or packaged in 25 kg bags. The 25 kg bags are assembled on a heat treated pallet to a net weight of 1'375 kg and covered with a stretch hood.

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of Borealis' products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

Stamylex[®] is a trademark of the Borealis Group.