



# Polyethylene Borlink™ LE7710

Thermoplastic Semiconductive Compound

## Description

**Borlink LE7710** is a thermoplastic black polyethylene compound, specially designed for semiconductive screen applications.

## Applications

**Borlink LE7710** is intended for semiconductive applications in medium voltage cables.

## Specifications

**Borlink LE7710** meets the applicable requirements as below when processed using sound extrusion practices and testing procedures

ISO 1872-E/BA, KHXY, 23-G200, C40

## Special features

**Borlink LE7710** is a ready-to-use black compound. The good distribution of carbon black and additives in Borlink LE7710 provides a chemically clean and smooth semiconductive screen.

## Physical Properties

Property	Typical Value	Test Method
	Data should not be used for specification work	
Density	1135 kg/m <sup>3</sup>	ISO 1183
Tensile Strain at Break (25 mm/min) <sup>1</sup>	200 %	ISO 527
Tensile Strength (25 mm/min) <sup>1</sup>	11 MPa	ISO 527
Change of Tensile Properties After Ageing (168 h, 135 °C) <sup>1</sup>	< 20 %	IEC 60811-401
Moisture	300 ppm	Karl Fischer-titration

<sup>1</sup> Measured on crosslinked specimens

## Electrical Properties

Property	Typical Value	Test Method
	Data should not be used for specification work	
DC Volume Resistivity (23 °C)	< 100 Ohm.cm	ISO 3915
DC Volume Resistivity (90 °C)	< 1000 Ohm.cm	ISO 3915

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168



# Polyethylene

# Borlink LE7710

## Processing Techniques

Borlink LE7710 provides excellent surface finish and outstanding output rates, when processing conditions are optimized for the actual processing equipment and cable dimensions. Optimal conditions may vary according to the equipment used.

### Extrusion

Typical processing temperature ranges for Borlink LE7710 are shown below:

Hopper drying (4 h)	60 °C	With dehumidified air
Melt temperature	120 - 185 °C	

## Packaging

Package:            Smallbins  
                         Octabins

## Storage

**Borlink LE7710** has a shelf life of 18 months from production date if stored in unopened original packages, under dry and clean conditions at temperatures between 10 - 30 °C (50 - 85 °F).

More information on storage is found in our "Safety data sheet" / "Product safety information sheet" for this product.

## Safety

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety of the product. For more information, contact your Borealis representative.



**Polyethylene**  
**Borlink LE7710**

**Disclaimer**

**The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.**

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

**Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.**

**It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.**

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.