



Polypropylene

BJ998MO

Description

BJ998MO -is a very high melt flow heterophasic copolymer with high/medium impact strength and stiffness. This grade is designed for high-speed injection moulding and contains nucleating and antistatic additives.

The material is nucleated with Borealis Nucleation Technology (BNT). Flow properties, nucleation and good stiffness give potential for cycle time reduction. Components moulded from this grade have good demoulding properties and combine good stiffness, gloss and antistatic properties with good low-temperature impact strength.

CAS-No. 9010-79-1

Applications

Thin wall containers
Square containers

Closures
Lids

Special features

High stiffness
High impact strength

Good gloss
Excellent antistatic properties

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	905 kg/m ³	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	100 g/10min	ISO 1133
Flexural Modulus	1.300 MPa	ISO 178
Tensile Modulus (50 mm/min)	1.400 MPa	ISO 527-2
Tensile Strain at Yield (50 mm/min)	5 %	ISO 527-2
Tensile Stress at Yield (50 mm/min)	25 MPa	ISO 527-2
Heat Deflection Temperature (0,45 N/mm ²)	100 °C	ISO 75-2
Charpy Impact Strength, notched (23 °C)	5 kJ/m ²	ISO 179/1eA
Charpy Impact Strength, notched (-20 °C)	3 kJ/m ²	ISO 179/1eA

Processing Techniques

This product is easy to process with standard injection moulding machines.

Following parameters should be used as guidelines:

Melt temperature	210 - 280 °C	Minimum to avoid sink marks.
Holding pressure	200 - 500 bar	
Mould temperature	10 - 30 °C	
Injection speed	As high as possible.	

Shrinkage 1 - 2 %, depending on wall thickness and moulding parameters

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



Polypropylene BJ998MO

Storage

BJ998MO should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety of the product.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"
Statement on compliance to food contact regulations
Statement on chemicals, regulations and standards
Recovery and disposal of polyolefins
Information on emissions from processing and fires



Polypropylene BJ998MO

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.