



Polypropylene BormedTM RB801CF-01

Description

Bormed RB801CF-01 is a random copolymer with high ethylene content.

The current version of Bormed RB801CF-01 has been scheduled for deletion.

Please refer to Bormed RB801CF-11 documentation for new projects.

In case of questions, please contact either your responsible Borealis Sales Manager and/or Application Development Engineer.

This grade is suitable for the manufacturing of non-oriented cast films on chill roll process and blown films on tubular water quenching process.

This grade is also suitable for blow moulding, including BFS technology and ISBM (1-stage process) for ampoules and bottles up to a maximum of 2 litres.

CAS-No. 9010-79-1

Applications

Bormed RB801CF-01 has been evaluated according to different regulations and norms. Typical applications are mentioned below for Medical devices or Pharmaceutical & Diagnostic packaging. However, Borealis should be consulted for final approval to evaluate the use of Bormed RB801CF-01 .

Medical device packaging
Pouches for Continuous Ambulatory Peritoneal Dialysis
Parenteral nutrition bags
Pouches for IV solutions

Secondary packaging
Ampoules/small bottles for eye, ear & nose drops
Bottles for IV-solutions
Bottles/ampoules for injectable solutions

This grade may only be used for the applications listed in the Product Datasheet and only to the extent that the application is within the scope of the tests set out in the Statement on Compliance to Regulations on Medical Use for that grade. If an application is not listed in the Product Datasheet, the grade can be used for such application only after express written consent of the Borealis Marketing Manager, Healthcare.
Borealis prohibits the use of any healthcare grade product in an implantable device that is introduced into the human body by surgical intervention and that is intended to remain in place following surgical procedure.

Special features

High gloss
Low haze
High softness
High impact strength
Low sealing initiation temperature
High water vapour barrier

Sterilisability by means of water steam
Good contact clarity
Sterilisability with EtO
Good gloss
Good surface finish

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



Polypropylene

Bormed RB801CF-01

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Melt Flow Rate (230 °C/2,16 kg)	1,9 g/10min	ISO 1133
Flexural Modulus ¹	750 MPa	ISO 178
Melting temperature (DSC)	140 °C	ISO 11357-3
Molecular weight distribution	Medium	

¹ Measured on injection moulded specimens, conditioned at 23 °C and 50 % relative humidity.

Film Properties

Specific film values evaluated on chill roll films, produced with Borealis internal standard conditions with a thickness of 50 µm. When compared to films which were produced under other conditions. It should be taken into account that the film properties are strongly dependent on the processing conditions.

Property	Typical Value	Test Method
Data should not be used for specification work		
Instrumented puncture test	Total Penetration Energy 32 J/mm	ISO 7765-2
Haze	< 1 %	ASTM D 1003
Gloss at 20 degree (of arc)	> 140	ASTM D 2457
Tensile Strain at Break	MD 540 %	ISO 527-3
Tensile Strain at Break	TD 600 %	ISO 527-3
Tensile Strength	MD 30 MPa	ISO 527-3
Tensile Strength	TD 30 MPa	ISO 527-3
Tensile Modulus	MD 400 MPa	ISO 527-3
Tensile Modulus	TD 400 MPa	ISO 527-3
Coefficient of friction (Film/Film)	> 0,7	ISO 8295

Storage

Bormed RB801CF-01 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet".

Safety

The product is not classified as dangerous. Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168

**Polypropylene**

Bormed RB801CF-01

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"

Statement on chemicals, regulations and standards

General statement on compliance to food contact regulations

Statement on compliance to regulations on medical use

Statement on polymer additives and BSE

Disclaimer

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168