



# Polypropylene HG385MO

## Description

**HG385MO** is a polypropylene homopolymer intended for injection moulding. This grade combines unique Borstar reactor design with Borealis Nucleation Technology (BNT) to produce highly-crystalline polypropylene. This product is characterized by excellent flow properties combined with a narrow molecular weight distribution well suited for low distortion products. This grade contains anti-static and slip additives, which result in short cycle time, good demoulding and low dust attraction.

Products moulded from this grade exhibit excellent dimension consistency combined with high stiffness.

**CAS-No.** 9003-07-0

## Applications

Caps and closures  
Items requiring good antistatic properties

## Special features

High stiffness  
Excellent antistatic properties

## Physical Properties

Property	Typical Value	Test Method
	Data should not be used for specification work	
Density	905 kg/m <sup>3</sup>	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	25 g/10min	ISO 1133
Flexural Modulus	1.550 MPa	ISO 178
Tensile Modulus (50 mm/min)	1.750 MPa	ISO 527-2
Tensile Strain at Yield (50 mm/min)	8 %	ISO 527-2
Tensile Stress at Yield (50 mm/min)	36 MPa	ISO 527-2
Heat Deflection Temperature (0,45 N/mm <sup>2</sup> ) <sup>1</sup>	105 °C	ISO 75-2
Charpy Impact Strength, notched (23 °C)	3 kJ/m <sup>2</sup>	ISO 179/1eA

<sup>1</sup> Measured on injection moulded specimens acc. to ISO 1873-2

## Processing Techniques

HG385MO is easy to process with standard injection moulding machines.

Following parameters should be used as guidelines:

Melt temperature	220 - 260 °C	
Holding pressure	200 - 500 bar	Minimum to avoid sink marks.
Mould temperature	10 - 30 °C	
Injection speed	As high as possible.	

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168



# Polypropylene HG385MO

Shrinkage 1 - 2 %, depending on wall thickness and moulding parameters

## Storage

**HG385MO** should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

## Safety

The product is not classified as dangerous.

## Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

## Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

Recovery and disposal of polyolefins

Information on emissions from processing and fires

"Safety data sheet" / "Product safety information sheet"

Statement on compliance to food contact regulations



**Polypropylene**  
**HG385MO**

**Disclaimer**

**The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.**

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

**Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.**

**It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.**

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.