



# Polypropylene HL712FB

## Description

**HL712FB** is a polypropylene homopolymer intended for fibre applications

**CAS-No.** 9003-07-0

## Applications

**HL712FB** is recommended for:

Micro denier fibres at high spinning speeds

Melt blown applications

## Special features

**HL712FB** is optimised to deliver:

Controlled rheology  
Easy processability

Optimal product consistency  
Very high flow

## Physical Properties

Property	Typical Value	Test Method
	<small>Data should not be used for specification work</small>	
Melt Flow Rate (230 °C/2,16 kg)	1.200 g/10min	ISO 1133
Melting temperature (DSC)	158 °C	ISO 11357-3
Molecular weight distribution	Very narrow	

## Storage

**HL712FB** should be stored in dry conditions at temperatures below 50°C and protected from UV-light.

Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet".

## Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety of the product. For more information, contact your Borealis representative.

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168



# Polypropylene HL712FB

## Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

## Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

Statement on chemicals, regulations and standards  
"Safety data sheet" / "Product safety information sheet"  
Statement on polymer additives and BSE  
General statement on compliance to food contact regulations

## Disclaimer

**The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.**

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

**Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.**

**It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.**

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.