



Polypropylene SA233CF

Description

SA233CF is a very soft random heterophasic copolymer.

This grade is suitable for use on conventional blown film lines with air cooling.

CAS-No. 9010-79-1

Applications

SA233CF is designed for:

Hygienic film
Lamination films
Multi layer co-extrusion films

Frozen food packaging
Heavy-duty bags
Soft packaging films

Special features

SA233CF is optimised to deliver:

Superior softness
Outstanding mechanical properties
Excellent heat seal properties

Easy processing on standard blown film lines with air-cooling

Physical Properties

Property	Typical Value	Test Method
	Data should not be used for specification work	
Melt Flow Rate (230 °C/2,16 kg)	0,8 g/10min	ISO 1133
Flexural Modulus ¹	500 MPa	ISO 178
Melting temperature (DSC)	140 °C	ISO 11357-3
Molecular weight distribution	Medium	

¹ Measured on injection moulded specimens, conditioned at 23 °C and 50 % relative humidity.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



Polypropylene SA233CF

Film Properties

Specific film values evaluated on blown films, produced with Borealis internal standard conditions with a thickness of 50 µm.

Property	Typical Value	Test Method
	Data should not be used for specification work	
Dart Drop	400 g	ISO 7765-1
Instrumented puncture test	Total Penetration Energy	15 J/mm
Haze	< 20 %	ISO 7765-2
Gloss at 20 degree (of arc)	> 8	ASTM D 1003
Tensile Strain at Break	MD 700 %	ASTM D 2457
Tensile Strain at Break	TD 800 %	ISO 527-3
Tensile Strength	MD 60 MPa	ISO 527-3
Tensile Strength	TD 50 MPa	ISO 527-3
Tensile Modulus	MD 500 MPa	ISO 527-3
Tensile Modulus	TD 500 MPa	ISO 527-3
Coefficient of friction	> 0,7	ISO 8295

Storage

SA233CF should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet".

Safety

The product is not classified as dangerous. Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"

Statement on chemicals, regulations and standards

Statement on compliance to food contact regulations

Statement on polymer additives and BSE

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



Polypropylene
SA233CF

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.