



# Polypropylene WG350C

## Description

**WG350C** is a polypropylene for extrusion coating.

**WG350C** is a filled polypropylene compound for extrusion coating. It can be used in standard extrusion coating lines although it is recommended to pre-dry **WG350C** before extrusion in order to avoid die build up. Standard conditions for drying are 90 °C / 4 hours.

**CAS-No.** 9002-88-4  
9003-07-0

## Applications

**WG350C** is recommended for:

Coated film  
Coating and lamination of aluminium foil

Peel layer for sterilisable food packaging

## Special Features

**WG350C** is optimised to deliver:

Seal- and peelable against Polypropylene

## Physical Properties

Property	Typical Value	Test Method
	Data should not be used for specification work	
Density	1040 kg/m <sup>3</sup>	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	18 g/10min	ISO 1133
Vicat softening temperature A50, (10 N) <sup>1</sup>	142 °C	ISO 306

<sup>1</sup> Measured on injection moulded specimens, conditioned at 23 °C and 50 % relative humidity.

## Processing Techniques

The actual conditions will depend on the type of equipment used.

A standard temperature setting would be:

Extruder 200 - 240 - 280°C  
Adapter, pipe 270°C  
Die 280°C

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168



# Polypropylene WG350C

## Storage

**WG350C** should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

## Safety

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

## Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

## Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"  
Statement on chemicals, regulations and standards  
Statement on compliance to food contact regulations

## Disclaimer

**The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.**

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

**Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.**

**It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.**

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168