

For more information and technical assistance contact:

Chevron Phillips Chemical Company LP
P.O. Box 4910
The Woodlands, TX 77387-4910
800.231.1212



BK10

K-Resin® Styrene-Butadiene Copolymers (SBC)

Customer Benefits

- Excellent Clarity
- Good Stiffness
- Good Toughness
- High Surface Gloss

Typical Applications

- Molded Containers and Bottles
- Medical Devices
- Overcaps
- Displays
- Toys

Nominal Physical Properties ⁽¹⁾	Condition	English	SI	Method
Specific Gravity	-	1.01 g/cc	1.01 g/cc	ASTM D792
Melt Flow Rate	200°C/5Kg	15.0 g/10 min	15.0 g/10 min	ASTM D1238
Tensile Yield Strength ⁽²⁾	2.0 in/min	3817 psi	26 MPa	ASTM D638
Tensile Elongation @ Break ⁽²⁾	2.0 in/min	248%	248%	ASTM D638
Flexural Modulus ⁽³⁾	0.5 in/min	242,000 psi	1668 Mpa	ASTM D790
Flexural Yield Strength ⁽³⁾	0.5 in/min	5160 psi	35.6 Mpa	ASTM D790
Deflection Temperature Under Load (DTUL)	264 psi (1.8 MPa)	140 °F	60 °C	ASTM D648
Instrumented Impact Total Energy ⁽⁴⁾	73 °F	364 in-lbs	41 J	ASTM D3763
Hardness, Shore D	-	62	62	ASTM D2240
Vicat Softening Point	-	180 °F	82 °C	ASTM D1525
Light Transmission	-	90 %	90 %	ASTM D1003

1. The nominal properties herein are typical of the product but do not reflect normal testing variance and therefore should not be used for specification purposes. Values are rounded.
2. Type 1 @ 2 in/min (50 mm/min)
3. 0.125 in (3.2 mm) specimen @ 0.5 in/sec (1.27 cm/min)
4. 0.125 in (3.2 mm) specimen @ 150 in/sec (381 cm/sec) impact rate

MEETS THESE IMPORTANT REQUIREMENTS:

- K-Resin® SBC grade BK10, as shipped by Chevron Phillips Chemical Company LP, meets the specifications of the United States FDA Food Packaging Regulation 21 CFR 177.1640 (polystyrene and rubber modified polystyrene). There are no regulatory food type or temperature restrictions on this resin.
- Commission Regulation (EU) No. 10/2011 and all its amendments.
- USP Class VI
- UL 94HB
- K-Resin® SBC grade BK10 is produced in an ISO 9001:2008 certified plant.

MSDS 100000000050

Revision Date February 2012

Another quality product from



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.