

For more information and technical assistance contact:

Chevron Phillips Chemical Company LP
P.O. Box 4910
The Woodlands, TX 77387-4910
800.231.1212



SUPERIOR FLEXIBLE PACKAGING RESINS

MarFlex® 7120B

HEXENE LINEAR LOW DENSITY POLYETHYLENE

This LLDPE is tailored for applications that require:

- Good stiffness at thin gauges
- Good drawdown
- Excellent processability
- Can use straight or in blends with LDPE or HDPE
- High amounts of slip agent

Typical blown and cast film applications include:

- Overwrap
- Coextrusions

Nominal Resin Properties	English	SI	Method
Density	---	0.919 g/cm ³	ASTM D1505
Melt Index, 190C/2.16Kg	---	2 g/10min	ASTM D1238
Process Aid	None	None	---
Antiblock	None	None	---
Slip	High	High	---

Nominal Cast Film Properties at 1.25 mil ¹	English	SI	Method
Haze	3 %	3 %	ASTM D1003
Gloss, 60°	140	140	ASTM D2457
COF	0.1	0.1	ASTM D1894
Dart	---	140 g/mil	ASTM D1709
Elmendorf Tear MD	---	300 g/mil	ASTM D1922
Elmendorf Tear TD	---	550 g/mil	ASTM D1922
Tensile Strength at Break MD	6200 psi	43 MPa	ASTM D882
Tensile Strength at Break TD	4800 psi	33 MPa	ASTM D882
Tensile Strength Elongation at Break MD	580 %	580 %	ASTM D882
Tensile Strength Elongation at Break TD	780 %	780 %	ASTM D882
1% Secant Modulus MD	29000 psi	200 MPa	ASTM D882
1% Secant Modulus TD	31000 psi	214 MPa	ASTM D882

1. Produced on 2.5 in extruder 24:1 L/D 25 mil Die Gap 520 F Melt Temperature

Revision Date February, 2008

Another quality product from



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.