

For more information and technical assistance contact:

Chevron Phillips Chemical Company LP
P.O. Box 4910
The Woodlands, TX 77387-4910
800.231.1212



SUPERIOR FLEXIBLE PACKAGING RESINS

MarFlex® 9608

EXTRUSION COATING BLENDING GRADE HIGH DENSITY POLYETHYLENE

This HDPE is tailored to blend with extrusion coating grade LDPE for applications that require:

- Excellent MVTR
- Improved stiffness properties
- Improved scuff resistance
- Good processibility
- Low gel levels
- Grease resistance

Typical extrusion coating applications may include:

- Moisture sensitive packaging
- Food packaging
- Blends
- Coextrusions
- Release liners

Nominal Resin Properties	English	SI	Method
Density	---	0.962 g/cm ³	ASTM D1505
Melt Index, 190C/2.16Kg	---	8 g/10min	ASTM D1238

Revision Date April, 2011

Another quality product from



Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.