

For more information and technical assistance contact:

Chevron Phillips Chemical Company LP  
P.O. Box 4910  
The Woodlands, TX 77387-4910  
800.231.1212



SUPERIOR FLEXIBLE PACKAGING RESINS

## MarFlex<sup>®</sup> 9656

High Density Polyethylene

### This HDPE is tailored for blown film applications that require:

- High Stiffness
- Excellent film drawdown
- Excellent processability
- Blending with LLDPE and LDPE

### Typical blown film applications include:

- Notion and millinery bags
- Multi-wall liners
- Coextrusions
- Overwraps

Nominal Resin Properties	English	SI	Method
Density	---	0.956 g/cm <sup>3</sup>	ASTM D1505
Melt Index, 190C/2.16Kg	---	0.75 g/10min	ASTM D1238

Nominal Blown Film Properties at 1 mil	English	SI	Method
COF	0.25	0.25	ASTM D1894
Dart	---	50 g/mil	ASTM D1709
Elmendorf Tear MD	---	13 g/mil	ASTM D1922
Elmendorf Tear TD	---	600 g/mil	ASTM D1922
Tensile Strength at Break MD	7400 psi	51 MPa	ASTM D882
Tensile Strength at Break TD	2600 psi	18 MPa	ASTM D882
Tensile Strength Elongation at Break MD	580 %	580 %	ASTM D882
Tensile Strength Elongation at Break TD	500 %	500 %	ASTM D882
1% Secant Modulus MD	122000 psi	841 MPa	ASTM D882
1% Secant Modulus TD	155000 psi	1069 MPa	ASTM D882
WVTR	0.31 g/100in <sup>2</sup> /day	4.8 g/m <sup>2</sup> /day	ASTM F1249
OTR	150 cm <sup>3</sup> /100in <sup>2</sup> /day	2300 cm <sup>3</sup> /m <sup>2</sup> /day	ASTM D3985

1. Produced using a grooved feed extruder at a rate of 8 lb/in die with a 2.5 BUR using a dual lip air ring

Revision Date October, 2007

Another quality product from



The Woodlands, Texas

Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Chevron Phillips Chemical Company LP does not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.